

X

इंटरनेट

### Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

"जानने का अधिकार, जीने का अधिकार" Mazdoor Kisan Shakti Sangathan "The Right to Information, The Right to Live"

"पुराने को छोड नये के तरफ" Jawaharlal Nehru "Step Out From the Old to the New"

मानक

### 

IS 101-6-3 (1990): Methods of sampling and test for paints, varnishes and related products, Part 6: Durability tests on paint films, Section 3: Moisture vapour permeability [CHD 20: Paints, Varnishes and Related Products]

> "ज्ञान से एक नये भारत का निर्माण″ Satyanarayan Gangaram Pitroda "Invent a New India Using Knowledge"

RIGHT TO INFORMATION "ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता Bhartrhari-Nītiśatakam "Knowledge is such a treasure which cannot be stolen"







611111111

Made Available By Public. Resource. Org







# BLANK PAGE



PROTECTED BY COPYRIGHT

IS 101 ( Part 6/Sec 3 ) : 1990

# भारतीय मानक

रंग रोगन, वार्निश तथा संबद्ध उत्पादों के नमूने लेने और परीक्षण की पद्धतियां

भाग 6 रंग-रोगन की परतों पर टिकाऊपन परीक्षण

अनुभाग 3 नमी वाष्प पारगम्यता

( तीसरा पुनरीक्षण )

Indian Standard

## METHODS OF SAMPLING AND TEST FOR PAINTS, VARNISHES AND RELATED PRODUCTS

### PART 6 DURABILITY TESTS ON PAINT FILMS

Section 3 Moisture Vapour Permeability

(Third Revision)

First Reprint MAY 1995

UDC 667<sup>.</sup>633 : 667.613<sup>.</sup>3 : 620<sup>.</sup>193<sup>.</sup>19

#### © BIS 1991

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

February 1991

Price Group 1

#### FOREWORD

This Indian Standard (Part 6/Sec 3) (Third Revision) was adopted by the Bureau of Indian Standards on 25 April 1990, after the draft finalized by the Paints and Allied Products Sectional Committee had been approved by the Chemical Division Council.

This standard is one of a series of standards on methods of sampling and test for paints, varnishes and related products. In the preparation of this standard, considerable assistance has been derived from ASTM D-1653.

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'.

### Indian Standard

### METHODS OF SAMPLING AND TEST FOR PAINTS, VARNISHES AND RELATED PRODUCTS

#### PART 6 DURABILITY TESTS ON PAINT FILMS

#### Section 3 Moisture Vapour Permeability

(Third Revision)

#### **1 SCOPE**

1.1 This standard (Part 6/Sec 3) prescribes the method to determine the rate at which moisture passes through films of paint, varnish and related products.

#### **2 DEFINITIONS**

Specific permeability of a film is the milligrams of water that permeate  $1 \text{ cm}^2$  of a 1 mm thick film in 24 h after a constant rate has been attained under conditions of 27°C and a difference in relative humidity across the film of approximately 100 percent.

#### **3 APPARATUS**

#### 3.1 Permeability Cup

A permeability cup that can be weighed in an analytical balance and will permit the exposure of 25 cm<sup>2</sup> of film to a condition of high humidity on one side and of low humidity on the other side. The cup shall have a capacity of approximately 25 ml and shall have a flanged edge. It shall be equipped with a separate corresponding flange so that the film may be held between them. The contacting faces of the flanges shall be ground to such flatness that when the film is in position, no moisture can be lost from the cup except through the 25 cm<sup>2</sup> of exposed area. For very hard film having a very rough surface, a soft rubber gasket may be inserted between the film and the flange. The flanges shall be held together securely with suitable clamps.

#### 3.2 Low-Humidity Chamber

A standard glass desiccator in which a desiccant may be placed which will produce a condition of very low relative humidity. The desiccant may be replaced with a salt solution of known vapour pressure when a condition of more than practically zero vapour pressure is required.

#### 3.3 Balance

An analytical balance, sensitivity of 1 mg.

#### 3.4 Temperature Control

Provision must be made to maintain the desiccator at a uniform temperature within  $\pm 1^{\circ}$ C of the specified temperature. The standard temperature of 27°C shall be used for normal conditions. Any other temperature may be used as required for special conditions if agreed upon by the purchaser and the supplier.

NOTE – Temperature control is important because of the rapid changes in relative humidity near 100 percent with small changes in temperature.

#### 3.5 Support for Film

For coatings that are too brittle or otherwise unsatisfactory for handling as free films, a suitable support shall be provided. Untreated, unplasticized cellophane is preferred, and such other materials as parchmentized paper and glass cloth may be used, if agreed upon by the purchaser and the supplier.

3.6 Desiccant, having a high affinity for water and a high drying efficiency, that is, giving a low water vapour pressure after absorbing a large amount of water. Phosphorus pentoxide ( $P_2O_6$ ), Calcium chloride (CaCl<sub>2</sub>) or magnesium perchlorate [Mg (ClO<sub>4</sub>)<sub>2</sub>] are preferred. The desiccant used shall be agreed upon by the purchaser and the supplier.

NOTE — Use caution in handling phosphorus pentoxide and magnesium perchlorate because of possible violent chemical reactions that may be produced if they come in contact with some materials.

#### 4 TEST SPECIMENS

4.1 The test specimens shall be smooth, completely continuous films of uniforms thickness throughout the test area and entirely free from dust or other foreign matter. The thickness of the coating applied shall be within normal range for the type of material under test and shall not vary by more than 5 percent of total thickness in any test series.

4.2 Air dry or bake the coated material for a specified time at a specified temperature which depend upon the requirements of the coating under test. Permeability may vary with the baking schedule or the time of air drying. If the

material is to be tested as a free film, remove it from the substrate and allow the previously unexposed surface free access to the air for at least 7 days in the case of air-drying materials.

#### 4.3 Preparation of Free Films

Hold the substrate with 25 mm thick tin foil rigidly so that its position is not disturbed during application operation. Over a clean, smooth and levelled surface, usually, a coating of known wet thickness is cast with an applicator. The method of application can be brush, spray, electrostatic electrodeposition, fluidisation and hot melt. After air drying or curing, place the substrate bearing the film in a mercury bath for amalga mation. Remove carefully the detached film from the bath.

NOTE  $\rightarrow$  A device equipped with a perforated metal plate for holding the substrate under vaccum, and a mechanical drive for drawing down the coating with an applicator, serves the purpose better than other modes of application.

4.4 Cut a circular disc from the conditioned free film or coated support by placing the cup on the material and cutting around the flange with a razor blade. Measure the thickness of the disc at several places with a suitable method. With supported films the mass of the support must be subtracted from the total mass of the disc. The amount of film on the 25 cm<sup>2</sup> under test may be calculated from the ratio of the total area of the disc to the 25 cm<sup>2</sup>.

4.5 When coatings are applied to one side only of a support, the coated side of the test specimen

shall be placed toward the water in the cup and the uncoated side exposed to the dry air of the desiccator.

#### **5 PROCEDURE**

5.1 Pour 6 to 8 ml of distilled water in the permeability cup, place the test specimen between the flanges, and adjust the clamps to hold it firmly in position. Place the coatings, with the coated side toward the water in the cup and the uncoated side exposed to the condition of low humidity. Weigh the loaded cup and place it in desiccator. Remove the cup for periodic weighing to determine the loss in mass due to moisture which has permeated through the 25 cm<sup>3</sup> area of the exposed test specimen. In general, the cup shall be weighed every 24 h for a period of one week or until the loss rate has become constant.

#### 6 CALCULATION

6.1 Plot the results of successive weighings against elapsed time and draw a smooth curve through the plotted points. When a straight line adequately fits the plot of four successive 24-h spaced points, a normally steady state exists. The slope of the straight line is the rate of vapour transmission for the test area.

6.2 Calculate the specific permeabitity to moisture as mg/cm<sup>2</sup> mm thickness for 24 h at approximately 100 percent relative humidity differential.

#### **Bureau of Indian Standards**

BIS is a statutory institution established under the Bureau of Indian Standards Act, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

#### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

#### **Review of Indian Standards**

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'.

This Indian Standard has been developed from Doc: No. CHD 20 (9601)

Amendments Issued Since Publication				
Amen	d No.	Date of Issu	e	Text Affected
·				
		BUREAU OF INDIA	N STANDARDS	
Headquar	ers:			
Manak Bh Telephone	avan, 9 Bahadur Shah s : 331 01 31, 331 13 7	Zafar Marg, New Del 5	hi 110002	Telegrams : Manaksanstha (Common to all offices)
Regional (	Offices :			Telephone
Central :	Manak Bhavan, 9 Ba NEW DELHI 11000	hadur Shah Zafar Mai 2	g	$ \left\{\begin{array}{r} 331\ 01\ 31\\ 331\ 13\ 75 \end{array}\right. $
Eastern :	1/14 C. I.T. Scheme CALCUTTA 700054	/II M, V. I. P. Road, N	<b>fanik</b> tola	37 84 99, 37 85 61           37 86 26, 37 86 62
Northern :	SCO 335-336, Sector	34-A, CHANDIGAR	H 160022	$ \left\{\begin{array}{c} 60 & 38 & 43 \\ 60 & 20 & 25 \end{array}\right. $
Southern :	C. I. T. Campus, IV C	Cross Road, MADRAS	5 600113	235 02 16, 235 04 42           235 15 19, 235 23 15
Western :	Manakalaya, E9 MII BOMBAY 400093	DC, Marol, Andheri (E	ast)	632 92 95, 632 78 58         632 78 91, 632 78 92
Branches :	AHMADABAD. COIMBATORE. FA JAIPUR. KANPUI	BANGALORE. I RIDABAD. GHAZIA R. LUCKNOW. PA	BHOPAL. ABAD. GUWAH TNA. THIRUV	BHUBANESHWAR. IATI. HYDERABAD. 'ANANTHAPURAM.