

X

इंटरनेट

# Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

"जानने का अधिकार, जीने का अधिकार" Mazdoor Kisan Shakti Sangathan "The Right to Information, The Right to Live"

"पुराने को छोड नये के तरफ" Jawaharlal Nehru "Step Out From the Old to the New"

IS 11239-2 (2009): Methods of Test for Rigid Cellular Thermal Insulation Materials, Part 2: Apparent Density [CHD 27: Thermal Insulation]



Made Available By Public.Resource.Org

611111111

मानक

RIGHT TO INFORMATION "ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता Bhartrhari-Nītiśatakam "Knowledge is such a treasure which cannot be stolen"

"ज्ञान से एक नये भारत का निर्माण″ Satyanarayan Gangaram Pitroda "Invent a New India Using Knowledge"





# BLANK PAGE



PROTECTED BY COPYRIGHT

IS 11239 (Part 2) : 2009 ISO 845 : 1988

भारतीय मानक दृढ़ जालीदार तापीय ऊष्मारोधी सामग्री की परीक्षण पद्धति भाग २ आभासी घनत्व ( पहला पुनरीक्षण )

Indian Standard METHOD OF TEST FOR RIGID CELLULAR THERMAL INSULATION MATERIALS PART 2 APPARENT DENSITY

(First Revision)

. ICS 83.100

© BIS 2009 BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

April 2009

Price Group 2

# Indian Standard

# METHOD OF TEST FOR RIGID CELLULAR THERMAL INSULATION MATERIALS

PART 2 APPARENT DENSITY

(First Revision)

#### 1 Scope

This international Standard specifies a method for determining the apparent overall density and the apparent core density of rigid cellular plastics, and the bulk density of semi-rigid and flexible cellular plastics and rubbers.

If the material to be tested includes skins formed during moulding, the apparent overall density or the apparent core density, or both, may be determined. If the material does not have skins formed during moulding, the term overall density is not applicable.

#### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards listed below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 291 : 1977, Plastics – Standard atmospheres for conditioning and testing.

ISO 1382 : 1982, Rubber - Vocabulary.

ISO 1923 : 1981, Cellular plastics and rubbers — Determination of linear dimensions.

#### **3** Definitions

For the purposes of this International Standard, the following definitions apply.

**3.1** apparent overall density (of a cellular material): The mass per unit volume of a sample, including all skins formed during moulding.

**3.2** apparent core density (of a cellular material) : The mass per unit volume of a sample after all skins formed during moulding have been removed.

~ .

**3.3** bulk density<sup>1)</sup> (of a cellular material) : The mass per unit volume of a material measured under specified conditions and including both permeable and impermeable voids present in the material.

#### **4** Apparatus

Ordinary laboratory apparatus and

4.1 Balance, capable of determining the mass of a test piece to an accuracy of 0,5 %.

4.2 Measuring instruments, in accordance with ISO 1923.

#### 5 Test pieces

#### 5.1 Dimensions

Each test piece shall be of a shape such that its volume can be easily calculated. It shall be cut without deforming the original cell structure of the material.

The size of a test piece should preferably be as large as possible, commensurate with the apparatus available and with the shape of the original material. For rigid materials, the total surface area of a test piece shall be at least 100 cm<sup>2</sup>. For semi-rigid and flexible materials, the volume of a test piece shall be at least 100 cm<sup>3</sup>.

For rigid materials, when the apparent overall density is being determined using test pieces cut from a larger sample, the ratio of the area of skin formed during moulding to total volume shall be the same for the test pieces as for the sample.

#### 5.2 Number of test pieces

A minimum of three test pieces shall be tested for flexible materials and a minimum of five shall be tested for rigid materials.

The sample may be a manufactured object whose mass and volume can be measured accurately. Its total mass and total volume may be used to determine the sample density (see 8.3).

<sup>1)</sup> See ISO 1382.

#### 5.3 Conditioning

**5.3.1** Wait at least 72 h after manufacture before cutting from product samples the test pieces required for measurement pur poses

If required, this period may be reduced to 48 h or 16 h if experience shows that, 48 h or 16 h after manufacture, the difference in density compared with the density 72 h after manufacture is less than 10 %.

5.3.2 The test pieces shall be kept for at least 16 h at ambient conditions or in a desiccator (dry conditions) as defined below. This conditioning period may be part of the 72 h period follow ing manufacture.

Ambient conditions in accordance with ISO 291:

23 °C ± 2 °C, 50 % ± 5 % relative humidity

or

27 °C + 2 °C, 65 % ± 5 % relative humidity

Dry conditions ·

23 "C + 2 "C

or

27 °C 1 2 'C

#### 6 Procedure

**6.1** Measure the dimensions, in millimetres, of the test pieces in accordance with ISO 1923. Make a minimum of three separate measurements of each dimension. For rigid materials in board form, make at least five measurements of the central area. Calculate the mean values for each dimension and from these measurements calculate the volumes of the test pieces.

6.2 . Weigh each test piece to an accuracy of 0.5 % and record its mass in grams

#### 7 Expression of results

7.1 The density  $\rho_a$  (apparent overall density, apparent core density or bulk density) of a test piece, in kilograms per cubic metre, is given by the formula

$$\frac{m}{V} \times 10^{6}$$

where

- m is the mass in grams, of the test piece
- I is the volume, in cubic millimetres, of the test piece.

Calculate the mean value of the density from the results for all test pieces and round it to the nearest 0,1 kg/m<sup>3</sup>.

NOTE With certain low-density closed-cell materials, for example those with densities less than 30 kg/m<sup>3</sup>, buoyancy may be a cause of error. Allowance for this factor may be made as follows:

$$\varphi_a = \frac{m + m_a}{1} \times 10^6$$

where

 $m_{\rm a}$  is the mass, in grams, of displaced air, calculated by multiplying the volume, in cubic millimetres, of the test piece by the density, in grams per cubic millimetre, of air at atmospheric temperature and pressure. The density of air at a temperature of 23 °C and a pressure of 101 325 Pa (760 mmHg) is 1,220  $\times$  10<sup>-6</sup> g/mm<sup>3</sup>; the density of air at 27 °C and 101 325 Pa is 1,195 5  $\times$  10<sup>-6</sup> g/mm<sup>3</sup>.

7.2 Calculate the standard deviation (estimated) as follows and report it to two significant figures:

$$s = \left| \frac{\sum x^2 - nx^2}{n-1} \right|$$

where

- s is the estimated standard deviation;
- is the value of a single measurement;
- r is the arithmetic mean of the set of measurements;
- n is the number of measurements made.

#### 8 Precision

**8.1** The values given in this clause were developed from data obtained using rigid materials only and with test pieces conditioned for 72 h. Their validity for other materials and condition ing periods has yet to be determined.

8.2 Inter- and intra laboratory precision of this test method can be expected to vary for different materials. Results of a five laboratory round robin test programme showed that, for certain materials, measured absolute density differences can be limited to 1,7 % (at 95 % confidence) within a single laboratory. Measured absolute density differences between laboratories can be limited to 2,6 % (at 95 % confidence) for the same materials.

8.3 The density of an item measured as a whole should agree to within 4 % with the density measured by cutting five test pieces from the whole, for a single laboratory and material.

NOTE - The above data are based upon results from a round-robin test programme between five laboratories in the USA and reported in ASTM Research Report RR: D-20 1105 of the American Society for Testing and Materials. The most variable material included in the round robin tests showed measured absolute differences in density of 8.4 within a laboratory and 15.3 between laboratories (at 85.% confidence).

# 9 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) a complete identification of the material tested;

c) the temperature and humidity at which the test pieces were conditioned;

d) the presence or absence of surface skins and if skins were removed for testing;

e) the presence of densification, striations or other defects of the test pieces,

f) the individual test results, stating details of test piece shape, test piece dimensions and the locations from which they were taken;

g) the mean value of the density (apparent overall density, apparent core density or bulk density) and the standard deviation;

 h) whether any allowance was made for buoyancy and, if so, the size of the correction and details of the temperature, pressure and relative humidity of the ambient air during the test;

any deviation from the procedure specified in this International Standard.

GMGIPN-35 BIS/ND/09-300

# NATIONAL FOREWORD

This Indian Standard (Part 2) (First Revision) which is identical with ISO 845: 1988 'Cellular plastics and rubbers — Determination of apparent (bulk) density' issued by the International Organization for Standardization (ISO) was adopted by the Bureau of Indian Standards on the recommendation of the Thermal Insulation Sectional Committee and approval of the Chemical Division Council.

This standard was originally published in 1985. This revision of the standard has been taken up to align it with ISO 845 : 1988 by adoption under dual numbering system.

The text of ISO Standard has been approved as suitable for publication as an Indian Standard without deviations. Certain conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear referring to this standard, they should be read as 'Indian Standard'
- b) Comma (,) has been used as a decimal marker in the International Standard while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

In this adopted standard, reference appears to the following International Standard for which Indian Standard also exists. The corresponding Indian Standard which is to be substituted in its place is listed below along with its degree of equivalence for the edition indicated:

International Standard	Corresponding Indian Standard	Degree of Equivalence
ISO 1923 : 1981 Cellular plastics and rubbers — Determination of linear dimensions	IS 11239 (Part 1):2009 Method of test for rigid cellular thermal insulation materials: Part 1 Dimensions ( <i>first</i> <i>revision</i> )	Identical

The technical committee responsible for the preparation of this standard has reviewed the provisions of the following International Standards has decided that they are acceptable for use in conjunction with this standard:

International Standard	Title
ISO 291 : 1977	Plastics - Standard atmospheres for conditioning and testing
ISO 1382 : 1982	Rubber Vocabulary

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'.

# **Bureau of Indian Standards**

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

# Copyright

BIS has the copyright of all its publications. No part of the these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

### **Review of Indian Standards**

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard alongwith amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc No.: CHD 27 (1532).

# Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected
A <u>-</u>	×	
		999) 1999 - San
· · · · · · · · · · · · · · · · · · ·		
		2

# BUREAU OF INDIAN STANDARDS

Manak Bhava Telephones:	an, 232	9 Bahadur Shah Zafar Marg, New Delhi 1100 3 0131, 2323 3375, 2323 9402 Webs	02 site : www.bis.org	.in	
Regional Of	fice	es :			Telephones
Central	;	Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002			2323 7617 2323 3841
Eastern	:	1/14 C.I.T. Scheme VII M, V.I.P. Road, Kank KOLKATA 700054	urgachi	2337 8499 2337 8626	2337 8561 2337 9120
Northern	:	SCO 335-336, Sector 34-A, CHANDIGARH 1	60022		{ 260 3843 \ 260 9285
Southern	:	C.I.T. Campus, IV Cross Road, CHENNAI 60	0113	{ 2254 1216   2254 2519	, 2254 1442 , 2254 2315
Western	:	Manakalaya, E9 MIDC, Marol, Andheri (East MUMBAI 400093	:)	{ 2832 9295 2832 7891	, 2832 7858 , 2832 7892
Branches	:	AHMEDABAD. BANGALORE. BHOPAL. BHUB GHAZIABAD. GUWAHATI, HYDERABAD, JA PARWANOO. PATNA. PUNE. RAJKOT. THIRU	ANESHWAR.COI AIPUR. KANPUR JVANANTHAPUF	MBATORE.F . LUCKNOW RAM.VISAKH	aridabad. . Nagpur. Iapatnam.