

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 7509 (1993): Thermal insulating cement [CHD 27: Thermal Insulation]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



भारतीय मानक

तापीय रोधन सीमेन्ट — विशिष्ट

(पहला पुनरीक्षण)

Indian Standard

THERMAL INSULATING CEMENTS —
SPECIFICATION

(*First Revision*)

UDC 662'998 : 666'946

© BIS 1993

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

FOREWORD

This Indian Standard was adopted by the Bureau of Indian Standards, after the draft finalized by the Thermal Insulation Materials Sectional Committee had been approved by the Chemical Division Council.

The material covered by this standard is in the form of dry powder, intended to be mixed with a suitable proportion of water, applied as a plastic mass, and dried in place, for use as insulation and not as a finishing cement.

The standard covers the specification of thermal insulating cements for use at limiting temperatures up to 350°C, 750°C and 950°C. Typical materials used are:

TYPE 350

- a) Hydrated magnesium carbonate and/or hydrated calcium silicate with suitable reinforcing fibres.
- b) Predominantly mineral wool fibres with suitable proportion of heat resistant binders.

TYPE 750

Hydrated calcium silicate and/or diatomaceous earth (silica) with suitable proportion of heat resistant binders and reinforcing fibres.

TYPE 950

Exfoliated vermiculite and/or diatomaceous earth (silica) with suitable proportion of heat resistant binders.

After the publication of IS 7509 : 1974 Thermal insulating cement (type 750), IS 7510 : 1974 Thermal insulating cement (type 350) and IS 9350 : 1980 Thermal insulating cement (type 950) covering thermal insulating cements for the range from 350°C to 950°C — the Committee decided to amalgamate the three standards into one.

The Committee responsible for the preparation of this standard is given at Annex B.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

THERMAL INSULATING CEMENTS — SPECIFICATION

(First Revision)

1 SCOPE

This standard prescribes requirements and method of sampling and test for thermal insulating cements for use at temperatures up to 950°C.

2 REFERENCES

The following Indian Standards are the necessary adjuncts to this standard:

IS No.	Title
3069 : 1965	Glossary of terms, symbols and units relating to thermal insulation materials
3346 : 1980	Method for the determination of thermal conductivity of thermal insulation materials (two slab guarded hot plate method) (<i>first revision</i>)
4905 : 1968	Methods for random sampling
5724 : 1970	Methods of test for thermal insulating cements
9490 : 1980	Method for determination of thermal conductivity of insulation materials (water colorimeter method)

3 TERMINOLOGY

3.1 For the purpose of this standard, the definitions of terms, symbols and units given in IS 3069 : 1965 and the following shall apply.

3.1.1 Consistency of Wet Mixed Thermal Insulating Cement

The degree at which it resists deformation due to the application of outside force.

4 TYPES

The material shall be of three types, viz,

- Type 350 for use of temperatures up to 350°C,
- Type 750 for use of temperatures up to 750°C, and
- Type 950 for use of temperatures up to 950°C.

5 REQUIREMENTS

5.1 The material shall be in the form of dry powder and/or granulated aggregate.

5.2 The material shall conform to the requirements given in Table 1 when tested in accordance with the methods referred to in col 6 of the table.

Table 1 Requirements of Thermal Insulating Cements

Sl No.	Characteristic	Requirements			Method of Test, Ref to Cl in IS 5724 : 1970
		Type 350°C	Type 750°C	Type 950°C	
(1)	(2)	(3)	(4)	(5)	(6)
i)	Service temperature	350°C	750°C	950°C	—
ii)	Consistency, percent				5
	a) Method A	35 to 45	35 to 45	—	
	b) Method B	175 to 230	175 to 235	—	
iii)	Dry covering capacity m ² , 1 cm, in thickness per 100 kg of dry cement, <i>Min</i>	17.5	20.0	14.0	6
iv)	Compressive strength at 5 percent deformation, kg/kg/cm ² , <i>Min</i>	3.5	3.5	5.0	7
v)	Volume change (shrinkage) upon drying, percent, <i>Max</i>	25	25	30	6
vi)	Linear shrinkage (length) after heat soaking at service temperature, percent, <i>Max</i>	2.0	3.0	3.0	9
vii)	Dry adhesion to steel, kg/cm ² , <i>Min</i>	0.35	0.85	0.50	10
viii)	Thermal conductivity W/mK, <i>Max</i>		3346 : 1980		9490 : 1980/
	Mean Temp, °C				
	100	0.09	0.07	0.14	
	200	0.11	0.09	0.16	
	300	—	0.11	0.18	
	400	—	—	0.20	

6 PACKING AND MARKING

6.1 Packing

The material shall be packed as agreed to between the purchaser and the supplier. However, polyethylene bonded hessian bags or paper lined hessian bags are generally used.

6.2 Marking

Packages shall be legibly and indelibly marked with the following information:

- a) Indication of the source of manufacture;

- b) Net mass of the contents;
- c) Name and type of the material;
- d) Amount and method of adding water, method of curing and drying; and
- e) Batch number and year of manufacture.

7 SAMPLING

The method of drawing representative samples of the material and criteria for their conformity shall be as prescribed in Annex A.

ANNEX A

(Clause 7)

SAMPLING OF THERMAL INSULATING CEMENTS

A-1 SCALE OF SAMPLING

A-1.1 Lot

All bags of insulating cement belonging to the same batch of manufacture, in a single consignment, shall be grouped together and each such group shall constitute a lot.

A-1.2 For ascertaining the conformity of the lot to the requirements of this specification tests shall be carried out on each lot separately.

A-1.3 The number of bags to be selected (n) shall depend on the lot size (N) and shall be in accordance with Table 2.

A-1.3.1 These bags shall be selected at random. In order to ensure the randomness of selection, random sampling procedures given in IS 4905 : 1968 may be adopted.

Table 2 Number of Bags to be Selected for Sampling

(Clause A-1.3)

Lot Size (N)	No. of Bags to be Selected (n)
Up to 25	1
26 to 50	2
51 to 100	3
101 and above	4

A-2 PREPARATION OF TEST SAMPLE AND NUMBER OF TESTS

A-2.1 From each of the bags selected according to A-1.3 approximately equal quantity of the material shall be taken and thoroughly mixed to form a composite sample weighing not less than 45 kg which would be sufficient for carrying out triplicate determination of all characteristics given in Table 1.

A-2.1.1 The composite sample shall be divided into three equal parts, one for the purchaser, another for the supplier and the third to be used as the referee sample.

A-2.1.2 These three parts of the composite sample shall be transferred to separate sample bags. These bags shall be properly stitched and labelled with full identification particulars.

A-2.1.3 The referee test sample shall bear the seal of both the purchaser and the supplier. It shall be kept at a place agreed to between the purchaser and the supplier to be used in case of any dispute between the two.

A-2.2 Tests for determination of all characteristics given in Table 1 shall be conducted on the composite sample.

A-3 CRITERIA FOR CONFORMITY

A-3.1 The lot shall be declared as conforming to the requirements of this specification if all the test results on the composite sample satisfy the corresponding requirements given in Table 1.

ANNEX B

(Foreword)

COMMITTEE COMPOSITION

Thermal Insulation Materials Sectional Committee, CHD 027

Chairman

PROF B. C. RAYCHAUDHURI
B-138, Sarita Vihar, New Delhi-110044

Members

SHRI K. N. AGARWAL
SHRI S. C. AGARWAL
SHRI J. P. KARDAM (*Alternate*)
SHRI M. P. CHITRE
SHRI SOVNATH (*Alternate*)
SHRI M. K. CHOURASIA
SHRI A. K. DASGUPTA
SHRI M. S. MUKHOPADHYAY (*Alternate*)
SHRI JAPAN DUTTA
SHRI K. K. BHATNAGAR (*Alternate*)
SHRI R. N. GANJOO
SHRI B. JOSHI (*Alternate*)
SHRI G. GHOSH
SHRI S. A. BOHRA (*Alternate*)
SHRI A. K. GUPTA
SHRI AJAY GUPTA
SHRI S. BANSAL (*Alternate*)
SHRI G. C. PANDIT
SHRI L. N. BADRUKA (*Alternate*)
SHRI R. P. PUNJ
SHRI J. K. CHOPRA (*Alternate*)
SHRI G. R. RAJAGOPALAN
SHRI R. V. RAMACHANDRAN
SHRI D. PADMANABHA (*Alternate*)
REPRESENTATIVE
REPRESENTATIVE
DR H. C. ROY
DR S. P. S. KHALSA (*Alternate*)
SHRI P. ROY
SHRI B. DUARI (*Alternate*)
SHRI R. SACHDEVA
SHRI K. V. SINGH (*Alternate*)
SHRI R. SANKARAN
SHRI S. K. KUNDU (*Alternate*)
SHRI S. S. PHOGAT (*Alternate*)
SHRI A. SHARIF
SHRI R. SRINIVASAN (*Alternate*)
SHRI R. K. SINGHAL
SHRI JADAV DATTA (*Alternate*)
SHRI N. SRINIVAS
SHRI C. P. KHANNA (*Alternate*)
SHRI NIMISH V. SURA
SHRI V. A. SURA (*Alternate*)
SHRI T. UDAYA KUMAR
SHRI A. K. SEN (*Alternate*)
SHRI C. V. VENKATAKRISHNAN
SHRI V. P. WASON
SHRI K. N. BHATNAGAR (*Alternate*)
DR R. K. SINGH,
Director (Chem)

Representing

Central Building Research Institute, Roorkee
Ministry of Energy, Dept of Power, New Delhi
Indian Oil Corporation (R & P Division), New Delhi
Metallurgical and Engineering Consultants (India) Ltd, Ranchi
Steel Authority of India Ltd, Ranchi
Petroleum Conservation and Research Assn, Dehra Dun
BASF India Ltd, Bombay
Nuclear Power Corpn, Bombay
Hyderabad Industries Ltd, Hyderabad
U. P. Twiga Fibreglass Ltd, New Delhi
Minwool Insulation Ltd, Bombay
Punj Sons Pvt Ltd, New Delhi
Engineers India Ltd, New Delhi
Tata Consulting Engineers, Bombay
Desein Consultants Pvt Ltd, New Delhi
Ministry of Energy (Dept of Coal), New Delhi
Projects & Development India Ltd, Sindri
Bakelite Hylam Ltd, Bombay
Directorate General of Technical Development, New Delhi
BHEL, Hyderabad
FPG Ltd, Bombay
NTPC, New Delhi
Lloyd Insulations (India) Pvt Ltd, New Delhi
Newkem Products Corporation, Bombay
PIBCO Limited, New Delhi
Beardsell Ltd, Madras
National Physical Laboratory, New Delhi
Director General, BIS (*Ex-officio Member*)

Member Secretary

SHRI SANJAY GUPTA
Assistant Director (Chem), BIS

Thermal Insulating Cements, Castable and Performed Thermal Insulation Products Subcommittee,
CHD 027 : 03

Convener

SHRI V. A. SURA

Newkem Products Corporation, Bombay

(Continued on page 4)

(Continued from page 3)

Members

DR K. N. AGARWAL
DR V. V. VERMA (*Alternate*)
SHRI C. S. ATHITHYAN
SHRI S. K. KUNDU (*Alternate*)
SHRI S. KANNAN (*Alternate*)
SHRI M.P. CHITRE

SHRI SOVNATH (*Alternate*)
SHRI A. K. GUPTA
SHRI DINESH KUMAR (*Alternate*)
SHRI K. KARKUN
SHRI PRANNAVASOURBAN
SHRI N. RAMANATHAN (*Alternate*)
SHRI R. P. PUNJ
SHRI J. K. CHOPRA (*Alternate*)
SHRI K. S. V. RAO
SHRI V. N. PANGAL (*Alternate*)
REPRESENTATIVE
SHRI NIMISH SURA
SHRI T. UDAYAKUMAR
SHRI A. K. SEN (*Alternate*)

Representing

Central Building Research Institute (CSIR), Roorkee
BHEL (Corporate R & D), Hyderabad

Indian Oil Corporation Ltd (Refinerics & Pipelines Division),
New Delhi

Hyderabad Industries Ltd, Hyderabad

PDIL, Sindri
Murugappa Morganite Ceramic Fibres Ltd, Madras

Punj Sons Pvt Ltd, New Delhi

Karnataka Explosives Ltd, Bangalore

Lloyd Insulations (India) Pvt Ltd, New Delhi
Newkem Products Corporation, Bombay
PIBCO Ltd, New Delhi

Standard Mark

The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'. Comments on this Indian Standard may be sent to BIS giving the following reference :

Doc : No. CHD 02 (79539)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha
(Common to all Offices)

Regional Offices :

Telephone

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 331 01 31 331 13 75
Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola CALCUTTA 700054	{ 37 84 99, 37 85 61 37 86 26, 37 86 62
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 53 38 43, 53 16 40 53 23 84
Southern : C. I. T. Campus, IV Cross Road, MADRAS 600113	{ 235 02 16, 235 04 42 235 15 19, 235 23 15
Western : Manakalaya, E9 MIDC, Marol, Andheri (East) BOMBAY 400093	{ 632 92 95, 632 78 58 632 78 91 632 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE.
FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR.
LUCKNOW. PATNA. THIRUVANANTHAPURAM.

AMENDMENT NO. 1 APRIL 1999
TO
IS 7509 : 1993 THERMAL INSULATING CEMENTS —
SPECIFICATION

(First Revision)

(Page 1, Table 1, col 3, heading) — Substitute 'Type 350' for 'Type 350⁰C'.

(Page 1, Table 1, col 4, heading) — Substitute 'Type 750' for 'Type 750⁰C'.

(Page 1, Table 1, col 5, heading) — Substitute 'Type 950' for 'Type 950⁰C'.

[Page 1, Table 1, Sl No. (iv), col 2] — Substitute ' kg/cm^2 ' for ' kg/kg/cm^2 '.

[Page 1, Table 1, Sl No. (vii), col 4] — Substitute '0.35' for '0.85'.

[Page 1, Table 1, Sl No. (viii), col 4] — Delete '3346 : 1980'.

[Page 1, Table 1, Sl No. (viii), col 6] — Substitute 'IS 9490 : 1980/ IS 3346 : 1980' for '9490 : 1980'.

(CHD 27)