

BLANK PAGE



IS: 10850 - 1984

Indian Standard SPECIFICATION FOR APPARATUS FOR MEASUREMENT OF WATER RETENTIVITY OF MASONRY CEMENT

UDC 666-946-5:620-193-19-05



© Copyright 1984

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

Indian Standard

SPECIFICATION FOR APPARATUS FOR MEASUREMENT OF WATER RETENTIVITY OF MASONRY CEMENT

Cement and Concrete Sectional Committee, BDC 2

Chairman

Representing

DR H. C. VISVESVARAYA

Cement Research Institute of India, New Delhi

Members

ADDITIONAL DIRECTOR, STAN- Research, Designs & Standards Organization DARDS (B&S) (Ministry of Railways), Lucknow

DEPUTY DIRECTOR, STAN-DARDS (B&S) (Alternate)

SHRI K. P. BANERJEE Larsen & Toubro Ltd, Bombay

SHRI HARISH N. MALANI (Alternate)

SHRI S. K. BANERJEE National Test House, Calcutta

DR N. S. BHAL Structural Engineering Research Centre (CSIR),
Roorkee

SHRI V. K. GHANEKAR (Alternate)

SHRI S. P. CHAKRABORTI Roads Wing, Ministry of Shipping and Transport,
New Delhi

SHRI M. SHIVAGURU (Alternate)
CHIEF ENGINEER (DESIGNS) Central Public Works Department, New Delhi
EXECUTIVE ENGINEER

(Designs) III (Alternate)

CHIEF ENGINEER (BD) Beas Designs Organization, Nangal Township Shri T. C. Basur (Alternate)

CHIEF ENGINEER (RESEARCH)- Irrigation Department, Government of Punjab, Cum-Director Chandigarh

RESEARCH OFFICER (IPRI)
(Alternate)

DR S. K. CHOPRA Cement Research Institute of India, New Delhi

DR A. K. MULLICK (Alternate)

DIRECTOR

A.P. Engineering Research Laboratories, Hyderabad

DIRECTOR A.P. Engineering Research Laboratories, Hyde Director (C & MDD-I) Central Water Commission, New Delhi

DEPUTY DIRECTOR (C & MDD-I)

(Alternate)

(Continued on page 2)

© Copyright 1984

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS: 10850 - 1984

(Continued from page 1)

Members

Representing

DIRECTOR	Central Soil & Materials Research Station, New Delhi			
DEPUTY DIRECTOR (Alternate)			
SHRI T. A. E. D'SA	The Concrete Association of India, Bombay			
SHRI N. C. DUGGAL (Alternat	e)			
Shri A. V. Gokak	Cement Controller, Ministry of Industry, New Delhi			
SHRI S. S. MIGLANI (Alternate				
SHRI A. K. GUPTA	Hyderabad Asbestos Cement Product Ltd, Hyderabad			
Shri N. G. Joshi	Indian Hume Pipes Company Ltd, Bombay			
SHRI P. J. JAGUS The Associated Cement Companies Ltd, Bombay				
Shri M. R. Vinayaka (Alternate)				
Shri S. R. Kulkarni	M.N. Dastur & Co Pvt Ltd, Bombay			
SHRI S. K. LAHA	The Institution of Engineers (India), Calcutta			
SHRI B. T. UNWALLA (Alterna				
SHRI G. K. MAJUMDAR	Hindustan Prefab Ltd, New Delhi			
SHRI H. S. PASRICHA (Alterna				
Shri K. K. Nambiar	In personal capacity ('Ramanalaya' 11 First Crescent Park Road, Gandhinagar, Adyar, Madras)			
SHRI Y. R. PHULL	Indian Roads Congress, New Delhi; and Central Road Research Institute (CSIR), New Delhi			
Shri M. R. Chatterjee	Central Road Research Institute (CSIR),			
(Alternate)	New Delhi			
SHRI K. L. SETHI (Alternate)				
DR MOHAN RAI	Central Building Research Institute (CSIR), Roorkee			
Dr S. S. Rehsi (Alternate)				
SHRI A. V. RAMANA	Dalmia Cement (Bharat) Ltd, New Delhi			
DR K. C. NARANG (Alternate				
SHRI G. RAMDAS	Directorate General of Supplies and Disposals, New Delhi			
Dr M. Ramaiah	Structural Engineering Research Centre (CSIR), Madras			
DR A. G. MADHAVA RAO (Alternate)				
DR A. V. R. RAO	National Buildings Organization, New Delhi			
SHRI J. SEN GUPTA (Alternate				
SHRI R. V. CHALAPATHI RAO SHRI S. ROY (Alternate)	Geological Survey of India, Calcutta			
SHRI ARJUN RIJHSINGHANI	Cement Corporation of India Ltd, New Delhi			
SHRI C. S. SHARMA (Alternate				
SHRI T. N. S. RAO	Gammon India Ltd, Bombay			
Shri S. A. Reddi (Alternate				
SHRI H. S. SATYANARAYANA	Engineer-in-Chief's Branch, Army Headquarters, New Delhi			
SHRI V. R. KOTNIS (Alternate				
SECRETARY	Central Board of Irrigation and Power, New Delhi			
SHRI K. R. SAXENA (Alternat				
SHRIK. A. SUBRAMANIAM	The India Cement Ltd, Madras			
SHRI P. S. RAMACHANDRAN (Public Works Department, Government of Tamil			
(Designs)	Nadu, Madras			
EXECUTIVE ENGINEER (SM &				
DIVISION) (Alternate)	••			
21.15.5.1 (/11.0.1.1.1)				
	(Continued on page 7)			

Indian Standard

SPECIFICATION FOR APPARATUS FOR MEASUREMENT OF WATER RETENTIVITY OF MASONRY CEMENT

0. FOREWORD

- **0.1** This Indian Standard was adopted by the Indian Standards Institution on 23 February 1984, after the draft finalized by the Cement and Concrete Sectional Committee had been approved by the Civil Engineering Division Council.
- 0.2 The Indian Standards Institution has formulated a series of standards on different types of cement and methods of tests of cement. As it was recognized that reliable or reproducible test results could be obtained only by using standard types of testing equipment which would give the desired level of accuracy, the Sectional Committee proposed to bring out a series of specifications covering the requirements of testing equipment to encourage the development and manufacture of standard testing equipment for cement testing in the country.
- **0.3** Accordingly, this standard has been prepared to cover requirements of apparatus for measurement of water retentivity of masonry cement. The relevant method of test is covered in IS:4031-1968*.
- **0.4** In addition to the apparatus described in this standard, the following are also required for conducting the test for measuring water retentivity of masonry cement:
 - a) Planetary mixer conforming to IS:10890-1984[†].
 - b) Flow table and accessories conforming to IS:5512-1983‡.
 - c) Tamping bar (see 9.3.5 of IS: 4031-1968*).

^{*}Methods of physical tests for hydraulic cement.

[†]Specification for planetary mixer used in tests of cement and pozzolana.

^{*}Specification for flow table for use in tests of hydraulic cements and pozzolanic materials (first revision).

IS: 10850 - 1984

0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS:2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard covers the requirements of apparatus used for measurement of water retentivity of masonry cement.

2. MATERIALS

2.1 The materials of construction of different components of the apparatus shall be as given in Table 1.

TABLE 1 MATERIALS OF CONSTRUCTION OF

DIFFERENT COMPONENTS SLCOMPONENT MATERIAL No. (1)(2)(3) Perforated dish Brass (plated) or any other material not i) attacked by masonry mortar Funnel Brass (plated) or any other material not ii) attacked by masonry mortar Flask Glass iii) iv) Filter paper Of a grade equivalent to Carl Schleicher & Schuell filter paper No. 576 or Whatman No. 50

3. CONSTRUCTION

3.1 Apparatus for the Water Retention Test — The assembly of the apparatus is shown in Fig. 1. The apparatus consists of a water aspirator or other source of vacuum controlled by a mercury column relief and connected by way of a three-way stopcock to a funnel upon which rests a perforated dish. The perforated dish shall be made of metal not attacked

^{*}Rules for rounding off numerical values (revised).


by masonry mortar. The metal in the base of the dish shall have a thickness of 1.7 to 1.9 mm and shall conform with the outline shown in Fig. 1. The bore of the stopcock shall have a 4 mm diameter, and the connecting glass tubing shall have a minimum inside diameter of 4 mm. A mercury manometer indicates the vacuum. A synthetic rubber gasket shall be permanently sealed to the top of the funnel and shall be lightly coated with petrolatum or light cup grease during a test to ensure a seal between the funnel and dish. Care shall be taken to ensure that none of the holes in the perforated dish are clogged from the grease used on the rubber gasket. Hardened filter paper of a grade equivalent to Carl Schleicher & Schuell filter paper No. 576 or to Whatman No. 50 filter paper shall be used. It shall be of such diameter that it will lie flat and completely cover the bottom of the dish.

3.2 Straightedge — Steel straightedge should not be less than 200 mm long, and not less than 1.5 mm nor more than 3 mm in thickness.

4. MARKING

- 4.1 The following information shall be clearly and indelibly marked on each component of the apparatus as far as practicable in way that it does not interfere with the performance of the apparatus:
 - a) Name of the manufacturer or his registered trade-mark or both, and
 - b) Date of manufacture.
- **4.1.1** The apparatus may also be marked with the ISI Certification Mark:

Note — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.



All dimensions in millimetres.

Fig. 1 Apparatus Assembly for Water Retention Test

(Continued from page 2)

Members

Representing

SHRI L. SWAROOP SHRI B. S. BHANDARI (Alternate)

Orissa Cement Ltd, New Delhi

SHRI G. RAMAN,

Director General, ISI (Ex-officio Member)

Director (Civ Engg)

Secretary

SHRI N. C. BANDYOPADHYAY Deputy Director (Civ Engg), ISI

Instruments for Cement and Concrete Testing Subcommittee, BDC 2:10

Convener

DR IQBAL ALI 14-1-359, New Aghapura, Hyderabad-500001

Members

SHRI P. D. AGARWAL

Central Public Works Department, Government of

DR T. N. CHOJER (Alternate)

Prof B. M. Ahuja SHRI S. K. BANERJEE

DR R. K. DATTA

Uttar Pradesh, Lucknow

Indian Institute of Technology, New Delhi National Test House, Calcutta

Central Building Research Institute (CSIR), Roorkee

SHRI J. P. KAUSHISH (Alternate) DIRECTOR

JOINT DIRECTOR (Alternate) EXECUTIVE ENGINEER (D) V SHRI T. P. EKAMBARAM

SHRI H. K. GUHA

A.P. Engineering Research Laboratories, Hyderabad

Central Public Works Department, New Delhi Highway Research Station, Madras

All India Instrument Manufacturers & Dealers Association, Bombay

DEPUTY SECRETARY (Alternate)

SHRI JATINDER SINGH SHRI GURCHARAN SINGH (Alternate)

Hydraulic Engineering Instruments, New Delhi

Associated Cement Companies Ltd, Bombay SHRI P. J. JAGUS SHRI D. A. WADIA (Alternate)

SHRI M. R. JOSHI

SHRI Y. P. PATHAK (Alternate)

PROF C. K. RAMESH

DR R. S. AYYAR (Alternate)

DR V. V. SUBBA RAO SHRI N. K. JAIN (Alternate) SHRI K. H. BABU (Alternate)

SHRI A. V. S. R. SASTRI

Indian Institute of Technology, Bombay

Ministry of Defence (R & D)

Cement Research Institute of India, New Delhi

Associated Instrument Manufacturers (India) Pvt Ltd, New Delhi; and Advisory Committee for Standardization of Instruments (ACSI), New Delhi

SHRI PALVINDER SINGH (Alternate)

Central Road Research Institute, New Delhi SHRI K. L. SETHI SHRI M. L. BHATIA (Alternate)

INDIAN STANDARDS

ON

INSTRUMENTS FOR TESTING CEMENT AND CONCRETE

5512-1983	Flow table for use in tests of hydraulic cement and pozzolanic materials (first revision)
5513-1976	Vicat apparatus (first revision)
5514-1969	Apparatus used in Le-Chatelier's test
5515-1983	Compaction factor apparatus (first revision)
5516-1969	Variable flow type air permeability apparatus (Blaine type)
5536-1969	Constant flow type air-permeability apparatus (Lee and Nurse type)
7320-1974	Concrete slump test apparatus
7325-1974	Apparatus for determination constituents of fresh concrete
9376-1979	Apparatus for measuring aggregate crushing value and ten percent fines value
9377-1979	Apparatus for aggregate impact value
9399-1979	Apparatus for flexural testing of concrete
9459-1980	Apparatus for use in measurement of length change of hardened cement paste, mortar and concrete
9799-1981	Pressure meter for determination of air content in freshly mixed concrete
10070-1982	Machine for abrasion testing of coarse aggregate
10078-1982	2 Jolting apparatus for testing cement
10079-1982	2 Cylindrical metal measures for use in tests of aggregates and concrete
10080-1982	2 Vibration machine
10086-1982	2 Moulds for use in tests of cement and concrete
10510-1983	3 Vee-bee consistometer