

X

इंटरनेट

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

"जानने का अधिकार, जीने का अधिकार" Mazdoor Kisan Shakti Sangathan "The Right to Information, The Right to Live"

"पुराने को छोड नये के तरफ" Jawaharlal Nehru "Step Out From the Old to the New"

मानक

IS 5246 (2000): Coniferous logs - [CED 9: Timber and Timber Stores]





"ज्ञान से एक नये भारत का निर्माण″ Satyanarayan Gangaram Pitroda "Invent a New India Using Knowledge"

"ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता Bhartrhari-Nītiśatakam "Knowledge is such a treasure which cannot be stolen"









51111111

Made Available By Public.Resource.Org



BLANK PAGE



PROTECTED BY COPYRIGHT

भारतीय मानक शंकुधारी लट्ठे — विशिष्टि (पहला पुनरीक्षण)

Indian Standard CONIFEROUS LOGS — SPECIFICATION (First Revision)

ICS 79.040

© BIS 2000

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

Price Group 3

FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Timber Sectional Committee had been approved by the Civil Engineering Division Council.

Specification for confireous sawn timber intended for further conversion is covered in IS 1909: 1991 'Specification for coniferous sawn timber (baulks and scantlings) (*fourth revision*)'; in order to select suitable logs for such sawn timber, it is felt by the Timber Sectional Committee, that for coniferous logs an Indian Standard should also be prescribed so that for such sawn timber suitable logs could be selected. This standard is formulated to give the minimun requirements of the three grades of coniferous logs, which are intended for further revision.

In the formulation of this standard due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country.

This standard was first published in 1969. Based on the experience gained, two amendments were issued to this standard. Besides incorporating these amendments, the evaluation of defects has been brought in line with IS 3364 (Part 1): 1976 'Methods of measurement and evaluation of defects in timber : Part 1 Logs (*first revision*)' in this revision.

This standard contains 7.1 which permits the purchaser to use his option for selection to suit his requirements at the time of placing orders.

The Committee responsible for the preparation of this standard is given at Annex A.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test of analysis, shall be rounded off in accordance with IS 2: 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard CONIFEROUS LOGS — SPECIFICATION (First Revision)

1 SCOPE

This standard covers the requirements of three grades of coniferous logs, that is, Grade 1, Grade 2 and Grade 3, for conversion into timber.

2 REFERENCES

The following standards contain provisions which through reference in this text, constitute provision of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standard indicated below:

IS No.	Title
707 : 1976	Glossary of terms applicable to timber technology and utilization (<i>second</i> <i>revision</i>)
1141 : 1993	Code of practice for seasoning of timber (second revision)
3364 (Part 1) : 1976	Method of measurement and evaluation of defects in timber : Part 1 Logs (<i>first revision</i>)

3 TERMINOLOGY

3.1 For the purpose of this standard the definitions given in IS 707 and the following shall apply.

3.2 Crack

An actual rupture of the wood tissues, that is a separation of the fibres in the longitudinal direction.

3.3 Hollow Centre

A log is said to be affected with hollow centre, when its centre heart (pith) is partially or completely removed with or without partial removal of the heart wood.

4 GRADES

The coniferous logs shall be classified in three grades, namely Grade 1, Grade 2 and Grade 3, on the basis of permissible defects as shown against each grade of logs for every 2.5 m length.

- Grade 1 6 minor defects or 2 major and 2 minor defects
- Grade 2 9 minor defects or 3 major and 3 minor defects

Grade 3 — 12 minor defects or 3 major and 6 minor defects

5 SPECIES

The logs shall be of the species of timber listed below:

Trade Name	Botanical Name Abl	breviation
Fir	Abies pindrow Royle	FIR
Deodar	Cedrus deodara D. Don	DEO
Cypress	Cupressus torulosa D. Don	CYP
Spruce	Picea Smithiana Boiss	SPR
Kail	Pinus excelsa Wall	KAL
Khasi Pine	Pinus Khasya Royle	KPI
Chir	Pinus Roxburghii Sargent	CHR

6 GENERAL REQUIREMENTS

The logs shall be free from hollow centre above 15 percent of the basal area of the log, spiral grain, any kind of decay (rot), insect attack and any other defects (except those permitted in 8). The hollow centre throughout the length of the log shall not be permitted.

7 DIMENSIONS AND MEASUREMENT

7.1 Dimensions

The logs shall be of the following dimensions:

Minimum length	2.5 m
Minimum mean mid-girth	100 cm

NOTE — Dimensions of logs less than the above may be permitted, if so, desired by the purchaser.

7.2 Measurement

The measurement of length and girth and the calculation of volume of logs shall be made as in 7.2.1 to 7.2.3.

7.2.1 Length

It shall be taken as the shortest distance in metres from one extreme end to the other. The length shall be rounded off to the nearest lower 0.05 m.

7.2.2 Mean Girth

In a log of regular taper, the mean girth shall be measured at the mid-length of a log but not over the bark or any protuberances. The girth shall be measured in centimetres and rounded off to the nearest lower centimetre. 7.2.2.1 In a log of irregular taper, three measurements shall be taken, that is one near the mid-length and at each end but not over the bark or any protuberance, the mean girth being obtained by taking the average of these measurements.

7.2.2.2 If girth measurements are taken over the bark, a deduction of 10 percent of mean girth, shall be made from the mid-girth on account of the bark.

7.2.3 Volume

The volume of logs shall be calculated by the quarter girth formula, as given below, the volume shall be expressed in cubic metre correct to three decimal places :

$$V = \left[\frac{G}{4}\right]^2 \times L$$

where

 $V = \text{Volume in } \text{m}^3,$

G = Girth in m, and

L = Length in m.

8 PERMISSIBLE DEFECTS IN LOGS AND THEIR EVALUATION

8.1 Defects to the extent, specified below, shall be permissible; plugging of defects shall not be permissible. All defects shall be measured as in 1S 3364 (Part 1).

8.1.1 Lack of Straightness

For every 2.5 m length of the log measured from its butt end:

- a) A deviation up to 25 mm from No defect the straight
- b) A deviation over 25 mm and A minor up to 50 mm from the straight defect
- c) A deviation over 50 mm and A major up to 100 mm from the straight defect
- 8.1.2 Taper

For every 2.5 m length of the log measured from its butt end:

a)	A taper up to 200 mm	No defect
b)	A taper over 200 mm and up to 250 mm	A minor defect
e)	A taper over 250 mm and up to	A maior

c) A taper over 250 mm and up to A major 300 mm defect

8.1.3 End Splits

The longest end split at each end shall be measured and the lengths added together. For every 2.5 m length of the log:

- a) The total length of the longest No defect splits up to 125 mm
- b) The total length of the longest A minor splits over 125 mm and up to defect 190 mm
- c) The total length of the longest A major splits over 190 mm and up to defect 250 mm

8.1.4 Surface Cracks

The depth of any crack shall not exceed 50 mm at any place on a log.

- 8.1.5 Cup Shakes (Ring Shakes)
 - a) A cup/ring shake visible only A minor on one end and located within defect
 50 mm from the centre heart (pith) of a log
 - b) A cup/ring shake visible on both the ends and located within 50 mm from the centre heart (pith) of a log (for each end)
 - c) A cup/ring shake visible only A major on one end and whose length, defect when measured along the arc, exceeds 230 mm
- 8.1.6 Knots
 - a) Live knots measuring up to No defect 75 mm in diameter
 - b) Live knots measuring over A minor 75 mm and up to 100 mm in diameter and occurring not more than 6 in number in a length of 2.5 m
 - c) Live knots measuring over A major 100 mm and up to 125 mm in defect diameter and occurring not more than 6 in number in a length of 2.5 m (see Note)
 - d) Dead knots measuring up to No defect
 75 mm in diameter and occurring not more than 2 in number in a length of 2.5 m
 - e) Dead knots measuring over A minor 75 mm and up to 125 mm in defect diameter and occurring not more than 4 in number in a length of 2.5 m

 f) Dead knots measuring over A major 125 mm and up to 150 mm in diameter and occurring not more than 4 in number in a length of 2.5 m

NOTE — Live knots measuring over 150 mm and up to 250 mm in diameter and occurring not more than 2 in number shall be allowed, provided they are not nearer than 2.0 m from the butt end of a log.

8.1.7 Hollow Centre

- a) Not more than 10 percent of the A minor basal area of the log and not defect extending throughout the length of the log
- b) More than 10 percent but not A major above 15 percent of the basal defect area of the log and not extending throughout the length of the log

8.1.8 Wounds

Wounds shall not be numerous or so grouped or located as to affect unduly the yield on conversion and usefulness of the sawn material. For the purpose of this standard, wounds shall be classified as under:

- a) Wounds upto 25 mm in depth No defect and upto 50 mm in diameter
- b) Wounds over 25 mm and upto A minor 40 mm in depth and upto 75 mm defect in diameter
- c) Wounds over 40 m and upto A major 50 mm in depth and over 75 mm defect

and upto 150 mm in diameter

9 END COATING

To protect and to minimize end cracking, splitting, etc, the ends of each log shall be adequately coated, up to a distance of at least 125 mm, with any of the materials mentioned in IS 1141. Application of end coating on the logs shall be done soon after the inspection of the log.

10 MARKING

10.1 Each log shall be legibly and indelibly marked at suitable place, preferably at the ends, to indicate the following:

- a) Abbreviation of the species,
- b) Supplier's identification mark and the year of supply,
- c) Length and mean girth of the log, and
- d) Grade.

10.2 BIS Certification Marking

10.2.1 Each log may also be marked with the Standard Mark.

10.2.2 The use of Standard Mark is governed by the provision of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. Details of conditions under which a licence for the use of the Standard Mark may be granted to the manufacturers or the producers may be obtained from the Bureau of Indian Standards.

ANNEX A

(Foreword)

COMMITTEE COMPOSITION

Timber Sectional Committee, CED 9

Chairman

SHRI SHYAM SUNDER 2989/D, 12th Main, HAL II Stage, Bangalore 560008

Members	Representing
Shri A. K. Ananthanarayana Shrimati B. S. Kamala (<i>Alternate</i>)	Institute of Wood Science and Technology, Bangalore
Shri Anil Agarwal Shri H. C. Pant (<i>Alternate</i>)	Ministry of Defence, Directorarte of Standardization, New Delhi
Shri S. M. Agarwal Shri B. B. Garg (<i>Alternate</i>)	WIMCO Ltd, New Delhi
Shri A. K. Bansal Shri K. Damodaran (<i>Alternate</i>)	Indian Plywood Industries Research & Training Institute, Bangalore
Shri G. P. Badola Shri Atul Khera (<i>Alternate</i>)	Forest Department, Government of Madhya Pradesh, Bhopal
Shri A. K. Chatterjee Shri O. P. Sharma (<i>Alternate</i>)	Directorate General of Technical Development, New Delhi
CHIEF CONSERVATOR OF FORESTS Additional Chief Conservator of Forests (Alternate	Forest Department, Government of Uttar Pradesh, Lucknow)
CHIEF CONSERVATOR OF FORESTS CONSERVATOR OF FORESTS (<i>Alternate</i>)	Himachal Pradesh Forest Department, Simla
CHIEF CONSERVATOR OF FORESTS (GENERAL)	Forest Department, Government of Karnataka, Bangalore
DIRECTOR (TRACK) JOINT DIRECTOR, CE (TM) (Alternate)	Ministry of Railways, New Delhi
Director	Forest Research Institute, Dehra Dun
DEPUTY DIRECTOR OF NAVAL ARCHITECTURE ASSISTANT DIRECTOR OF NAVAL ARCHITECTURE (Alternate	Naval Headquarters, New Delhi e)
Shri Erappa	The Karnataka State Forest Industries Corporation Limited, Bangalore
SHRI S. K. CHAKRABORTI (Alternate)	
DR K. GNANAHARAN	Kerala Forest Research Institute, Peechi
INSPECTOR GENERAL OF FORESTS Additional Inspector General of Forests (Alternate	Ministry of Environment and Forests, New Delhi)
Shri D. B. Jain Shri Darbara Singh (<i>Alternate</i>)	Directorate General of Supplies & Disposal, New Delhi
Shri D. K. Kanungo Shri B. K. Mandal (<i>Alternate</i>)	National Test House, Calcutta
SHRI S. KUMAR SHRI S. C. MALHOTRA (Alternate)	Andaman Chamber of Commerce & Industry, Port Blair
Shri P. T. S. Menon	Indian Plywood Manufacturing Co Ltd, Mumbai
Shri B. A. Mathews	Forest Department, Andaman & Nicobar Islands, Port Blair
SHRI A. MUKHERJEE SHRI A. K. AGARWAL (<i>Alternate</i>)	Directorate of Standardization, New Delhi
	(Continued on page 5)

4

(Continued from page 4)

Members

DR A. N. NAYER

SHRI R. C. PRASAD SHRI B. M. PRASAD (Alternate)

PRESIDENT EXECUTIVE DIRECTOR (Alternate)

SHRI S. S. RAJPUT

SHRI B. B. SHAMBARKAR SHRI A. K. AGARWAL (Alternate)

SHRI S. N. SHARMA

SHRI K. S. SHUKLA

SHRI N. M. WALECHA SHRI ANAND PRAKASH (Alternate)

SHRI S. S. SETHI, Director (Civ Engg)

Representing

In personal capacity (C-59 Inderpuri, New Delhi 110012)

Bihar State Forest Development Corporation Ltd, Patna

Federation of Indian Plywood and Panel Industry, New Delhi

Convener, Timber Terminology and Classification Subcommittee, CED 9:1; Timber Testing Subcommittee, CED 9:9; and Timber Conversion and Grading Subcommittee, CED 9:10

Engineer-in-Chief's Branch, New Delhi

Convener, Timber Seasoning and Treatment Subcommittee, CED 9:3

Forest Research Institute, Forest Products Division, Dehra Dun

Directorate General of Civil Aviation, New Delhi

Director General, BIS (Ex-officio Member)

Member-Secretary

SHRIMATI RACHNA SEHGAL Deputy Director (Civ Engg), BIS

Timber Conversion and Grading Subcommittee, CED 9:10

Convener	
Shri S. S. Rajput	Forest Products Division, Forest Research Institute, Dehra Dun
Member	
Shri A. K. Ananthanarayana Shrimati B. S. Kamala (<i>Alternate</i>)	Institute of Wood Science and Technology, Bangalore
Shri S. P. Badoni	Forest Research Institute, Dehra Dun
Shri J. L. Bandopadhyay	Directorate of Posts and Telegraph, New Delhi
CHIEF CONSERVATOR OF FORESTS Additional Chief Conservator of Forests (Alternate	Forest Department, Government of Uttar Pradesh, Lucknow)
CHIEF CONSERVATOR OF FORESTS CONSERVATOR OF FORESTS (Alternate)	Himachal Pradesh Forest Department, Shimla
CHIEF CONSERVATOR OF FORESTS CONSERVATOR OF FORESTS (<i>Alternate</i>)	Forest Department, Government of West Bengal, Calcutta
Shri K. Damodaran Shri H. Guruva Reddy (<i>Aliernate</i>)	Indian Plywood Industries Research & Training Institute, Bangalore
DIRECTOR (TRACK) JOINT DIRECTOR (TM) (<i>Alternate</i>)	Ministry of Railways, New Delhi
Shri G. L. Dua Shri M. A. Azeez (<i>Alternate</i>)	Rural Electrification Corporation Ltd, New Delhi
Dr R. Gnanaharan	Kerala Forest Research Institute, Peechi

(Continued from page 5) Representing Members U. P. Forest Corporation, Lucknow Shri P. N. Gupta SHRI B. K. SIKKA (Alternate) Himachal Pradesh State Forest Corporation, Shimla MANAGING DIRECTOR EXECUTIVE DIRECTOR (Alternate) Directorate of Standardization, New Delhi SHRI S. PANDEY SHRI J. P. BHARADWAJ (Alternate) ASCU Kickson Ltd, Calcutta SHRI RAJIV AGARWAL SHRI J. BASU (Alternate) Forest Research Institute, Dehra Dun Dr Satish Kumar DR INDRA DEV (Alternate) Directorate General of Civil Aviation, New Delhi SHRI F. C. SHARMA SHRI N. M. WALECHA (Alternate) Controllerate of Quality Assurance, Kanpur SHRI J. K. SINHA Bombay Timber Merchants Association, Mumbai Shri R. T. Somaiya SHRI JOMMY WADIA (Alternate) Directorate General of Supplies and Disposal, New Delhi SHRI N. K. UPADHYAY Forest Operation Division, Forest Research Institute, Dehra Dun SHRI V. K. WADHWA SHRI B. K. BHATIA (Alternate)

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

Headquarters:

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc : No. CED 9 (5757).

Amendments Issued Since Publication Amend No. Date of Issue Text Affected

BUREAU OF INDIAN STANDARDS

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110 002 Telegrams : Manaksanstha Telephones : 323 01 31, 323 33 75, 323 94 02 (Common to all offices) **Regional Offices :** Telephone Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg (323 76 17 **NEW DELHI 110 002** 323 38 41 Eastern 1/14 C. I. T. Scheme VII M, V. I. P. Road, Kankurgachi (337 84 99, 337 85 61 CALCUTTA 700 054 337 86 26, 337 91 20 SCO 335-336, Sector 34-A, CHANDIGARH 160 022 Northern : **f** 60 38 43 160 20 25 Southern : C. I. T. Campus, IV Cross Road, CHENNAI 600 113 (235 02 16, 235 04 42 235 15 19, 235 23 15 Western : Manakalaya, E9 MIDC, Marol, Andheri (East) (832 92 95, 832 78 58 MUMBAI 400 093 832 78 91, 832 78 92 Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM.

Printed at New India Printing Press, Khurja, India