

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”


IS 7779-2-2 (1979): Schedule of properties and availability of stones for construction purposes, Part II: Maharashtra state, Section 2: Engineering properties of building stones [CED 6: Stones]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard

SCHEDULE OF PROPERTIES AND
AVAILABILITY OF STONES FOR
CONSTRUCTION PURPOSES

PART II MAHARASHTRA STATE

Section 2 Engineering Properties of Building Stones

UDC 691.21 : 553.5 (083) (547.1)



© Copyright 1979

INDIAN STANDARDS INSTITUTION
MANAK BHAYAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Price Rs 7.00

Gr 4

September 1979

Indian Standard

SCHEDULE OF PROPERTIES AND AVAILABILITY OF STONES FOR CONSTRUCTION PURPOSES

PART II MAHARASHTRA STATE

Section 2 Engineering Properties of Building Stones

Stones Sectional Committee, BDC 6

Chairman

SHRI B. RAMACHANDRAN

Representing

Geological Survey of India, Calcutta

Members

SHRI S. R. PRADHAN (<i>Alternate to</i> Shri B. Ramachandran)	Builders' Association of India, Bombay
SHRI K. K. AGRAWALA	Delhi Marble Dealers' Association, New Delhi
SHRI K. K. MADHOK (<i>Alternate</i>)	Engineer-in-Chief's Branch (Ministry of Defence)
SHRI R. K. BANSAL	Central Public Works Department, New Delhi
SHRI J. K. CHARAN	Public Works Department, Government of Rajasthan, Jaipur
SHRI K. KAMLANATHAN (<i>Alternate</i>)	National Test House, Calcutta
CHIEF ARCHITECT	
CHIEF ENGINEER (B & R)	Department of Geology & Mining, Government of Rajasthan, Udaipur
SHRI G. C. DAS	
SHRI P. R. DAS (<i>Alternate</i>)	Public Works Department, Government of Uttar Pradesh, Lucknow
SHRI Y. N. DAVE	Public Works Department, Government of Orissa, Bhubaneswar
SHRI R. G. GUPTA (<i>Alternate</i>)	
DEPUTY DIRECTOR (RESEARCH), PWD RESEARCH INSTITUTE	Central Road Research Institute (CSIR), New Delhi
DEPUTY DIRECTOR (RESEARCH), CONTROL & RESEARCH LABORATORY	
DR M. P. DHIR	Public Works Department, Government of Gujarat, Ahmadabad
DR N. B. LAL (<i>Alternate</i>)	Central Water Commission, New Delhi
DIRECTOR, GERI, VADODARA	
DIRECTOR (CSMRS)	
DEPUTY DIRECTOR (CSMRS) (<i>Alternate</i>)	

(Continued on page 2)

© Copyright 1979

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 7779 (Part II/Sec 2) - 1979

(Continued from page 1)

Members

DIRECTOR, MERI, NASIK

RESEARCH OFFICER, MATERIAL
TESTING DIVISION, MERI,
NASIK (Alternate)

SHRI M. K. GUPTA

DR IQBAL ALI

SHRI A. B. LINGAM (Alternate)

SHRI P. J. JAGUS

SHRI R. C. JAIN

SHRI PREM SWARUP

SHRI A. K. AGARWAL (Alternate)

DR A. V. R. RAO

SHRI J. SEN GUPTA (Alternate)

SUPERINTENDING ENGINEER
(DESIGNS)

SUPERINTENDING ENGINEER
(DESIGNS)

DEPUTY CHIEF ENGINEER
(I & D) (Alternate)

SUPERINTENDING ENGINEER
(DESIGNS & PLANNING)

SUPERINTENDING ENGINEER
(PLANNING CIRCLE)

SUPERINTENDING SURVEYOR OF
WORKS

SHRI D. AJITHA SIMHA,
Director (Civ Engg)

Representing

Irrigation & Power Department, Government of
Maharashtra, Bombay

Himalayan Tiles and Marble Pvt Ltd, Bombay
Engineering Research Laboratories, Government of
Andhra Pradesh, Hyderabad

Institution of Engineers (India), Calcutta
Ministry of Shipping & Transport (Roads Wing)
Department of Geology & Mining, Government of
Uttar Pradesh, Lucknow

National Buildings Organization, New Delhi

Public Works & Electricity Department, Govern-
ment of Karnataka, Bangalore

Public Works Department, Government of Tamil
Nadu, Madras

Public Works Department, Government of Andhra
Pradesh, Hyderabad

Public Works Department, Government of West
Bengal, Calcutta

Public Works Department, Government of
Himachal Pradesh, Simla

Director General, ISI (Ex-officio Member)

Secretary

SHRI S. SENGUPTA

Assistant Director (Civ Engg), ISI

Indian Standard
**SCHEDULE OF PROPERTIES AND
AVAILABILITY OF STONES FOR
CONSTRUCTION PURPOSES**

PART II MAHARASHTRA STATE

Section 2 Engineering Properties of Building Stones

0. FOREWORD

0.1 This Indian Standard (Part II/Section 2) was adopted by the Indian Standards Institution on 30 January 1979, after the draft finalized by the Stones Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Stones are available in large quantities in different parts of the country. To choose and utilize them for various uses, it is necessary to know their availability as well as their various physical properties. Accordingly this Indian Standard is formulated to cover these informations. It is hoped that with the publication of this standard it will be convenient for the users to know the location of the various types of stones, and it will also act as a guide for their proper selection depending upon their particular use. This standard will give a general information for prospective builders who use stone and stone aggregates. The final acceptance of these materials in any work, would, however, be subject to the physical standards and other specification and quality control requirements stipulated for individual works.

0.2.1 This standard will be published in parts, each part covering a State. For facility in compilation and use of the standard, each part is divided in three sections. Accordingly Part II covers Maharashtra State and is being issued in three sections. Section 1 gives information on the availability of stones in the form of a map showing geological classification and location of known stone quarries; Section 2 covers engineering properties of building stones; and Section 3 covers engineering properties of stone aggregates.

0.3 The information contained in this section is based on the data provided by Engineering Research Institute, Maharashtra State and covers data collected up to the end of 1978. Further information, as and when received, will be added as addendum to this standard.

IS : 7779 (Part II/Sec 2) - 1979

0.4 In reporting the results of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS : 2-1960*.

1. SCOPE

1.1 This Standard (Part II/Section 2) covers engineering properties of building stones of Maharashtra State.

2. TEST RESULTS

2.1 The test results of building stones tested for some of the important properties according to relevant Indian Standards are given in Table 1.

*Rules for rounding off numerical values (*revised*).

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE

Sl. No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974‡)	Porosity, Percent (IS : 1124-1974‡)	Water Absorption, Percent (IS : 1124-1974‡)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability, Percent Loss (IS : 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
1. Ahmednagar															
	Bhandardara Dam Dn. Spillway Quarry	Compact basalt	Aphanitic	Greyish black	2.70	—	—	1.59	868.00	—	—	—	—	—	—
	do	do	do	do	2.70	—	—	1.60	715.00	—	—	—	—	—	—
	Bhandardara Dam Dn. Foundation of Buttress	do	do	do	2.80	—	—	1.40	1014.00	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	2.70	—	—	2.00	675.00	—	—	—	—	—	—
	do	do	do	do	2.60	—	—	2.40	634.00	—	—	—	—	—	—
	do	do	do	do	—	—	—	2.8	—	—	—	—	—	—	—
	do	do	do	do	—	—	—	2.00	—	—	—	—	—	—	—
	do	do	do	do	—	—	—	2.40	—	—	—	—	—	—	—
	do	Compact basalt	Aphanitic	do	—	—	—	1.40	—	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	—	—	—	3.00	—	—	—	—	—	—	—
	do	Compact basalt	Aphanitic	do	—	—	—	2.30	—	—	—	—	—	—	—
	Bhandardara Dam Foundation of Buttress	Zeolitic basalt	Amygdaloidal	do	2.66	—	—	2.80	553.00	—	—	—	—	—	—
	Bhandardara Dam Quarry Near Buttress	do	do	do	2.78	—	—	2.13	453.00	—	—	—	—	—	—
	do	do	do	do	2.64	—	—	3.16	478.00	—	—	—	—	—	—
	Bhandardara Dam Dn.	do	do	do	2.60	—	—	3.00	535.00	—	—	—	—	—	—
	Bhandardara Quarry	do	do	do	2.76	—	—	1.27	883.00	—	—	—	—	—	—
	do	Compact basalt	Aphanitic	do	—	—	—	2.07	—	—	—	—	—	—	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — *Contd*

SL No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974‡)	Porosity, Percent (IS : 1124-1974‡)	Water Absorption, Percent (IS : 1124-1974‡)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability, Percent Loss (IS : 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
	Bhandardara Quarry	Zeolitic basalt	Amygdaloidal	Greyish black	—	—	—	1·27	—	—	—	—	—	—	—
	Bhandardara	Compact basalt	Aphanitic	do	2·79	—	—	2·12	553·00	—	—	—	—	—	—
	Near Bhandardara Village	do	do	do	2·80	—	—	1·00	1227·00	—	—	—	—	—	—
	Quarry Near Prawara Project	Compact basalt	Aphanitic	do	2·70	—	—	1·10	979·00	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	2·80	—	—	1·40	822·00	—	—	—	—	—	—
	Shandi Ghat Quarry	Compact basalt	Aphanitic	do	2·99	—	—	1·91	751·00	—	—	—	—	—	—
	Kolarghati Road Quarry	do	do	do	2·79	—	—	1·20	1136·00	—	—	—	—	—	—
	Spillway Quarry	Zeolitic basalt	Amygdaloidal	do	2·70	—	—	1·53	635·00	—	—	—	—	—	—
	do	do	do	do	2·83	—	—	1·60	739·00	—	—	—	—	—	—
	Hill Slope Quarry	do	do	do	2·62	—	—	2·14	810·00	—	—	—	—	—	—
	do	do	do	do	2·72	—	—	1·37	1095·00	—	—	—	—	—	—
	Shundi Ghatghar Quarry	Compact basalt	Aphanitic	do	—	—	—	1·91	—	—	—	—	—	—	—
	Kolarghoti Road	do	do	do	—	—	—	1·20	—	—	—	—	—	—	—
	Quarry at Spillway Site	Zeolitic basalt	Amygdaloidal	do	—	—	—	2·13	—	—	—	—	—	—	—
	Quarry Near Buttress	do	do	do	—	—	—	3·16	—	—	—	—	—	—	—
	Near	Compact basalt	Aphanitic	do	—	—	—	1·00	—	—	—	—	—	—	—
2.	Akola														
	Akola	do	do	do	2·90	—	—	0·31	2247·00	—	—	—	—	—	—
	do	Deccan Trap	Fine grained compact basalt	Light grey	2·95	2·90	1·73	0·31	2247·00	258·00	512·00	1·08	+30·30	—0·192	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

SL No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974‡)	Porosity, percent (IS : 1124-1974‡)	Water Absorption, percent (IS : 1124-1974‡)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability, percent Loss (IS : 1126-1974)	Change in Absorption, percent	Change in Volume, percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
	B & C Dn. Murtizapur	Zeolitic basalt	Amygdaloidal	Greyish black	2.83	—	—	0.77	827.00	—	—	—	—	—	—
	do	do	do	do	—	—	—	0.77	—	—	—	—	—	—	—
3.	Amravati														
	Amravati	Compact basalt	Aphanitic	do	2.80	—	—	1.76	755.00	—	—	—	—	—	—
	Wadi Quarry	Deccan trap	Fine grained basalt	Black	2.09	2.80	6.87	1.76	755.00	177.00	650.00	0.51	-46.59	-0.060	—
4.	Aurangabad														
	Aurangabad	Compact basalt	Aphanitic	Greyish black	2.67	—	—	3.02	693.00	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	2.67	—	—	1.41	344.00	—	—	—	—	—	—
	Aurangabad Nagar Road 7 Miles	Deccan trap	Fine grained amygdaloidal porphyritic basalt	Black	2.98	2.67	10.47	1.41	344.00	121.00	216.00	1.32	-13.21	-0.771	Surface of specimens became rough at the end of 20 cycles of durability
	Hoshangate Quarry	Deccan trap	Medium grained compact basalt	Grey	2.95	2.67	9.41	3.02	603.00	—	—	2.86	-10.13	-0.355	Surface became rough after durability test
5.	Buldhana														
	Jambudhota Quarry	Compact basalt	Aphanitic	Greyish black	2.82	—	—	3.10	561.00	—	—	—	—	—	—
	Kund Quarry	do	do	do	2.80	—	—	3.27	673.00	—	—	—	—	—	—
6.	Bhir														
	Bhir	do	do	do	2.88	—	—	0.53	2290.00	—	—	—	—	—	—
	Rajuri Quarry	Deccan trap	Fine grained compact basalt	Dark grey	3.00	2.88	3.94	0.53	2290.00	339.00	201.00	0.06	-26.45	+0.032	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

SL No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974‡)	Porosity Percent (IS : 1124-1974‡)	Water Absorption, Percent (IS : 1124-1974‡)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability, Percent Loss (IS : 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
7.	Bombay														
	Bombay	Compact basalt	Aphanitic	Greyish black	2.97	—	—	0.34	862.00	—	—	—	—	—	—
	Andheri	Deccan trap	Medium grained basalt	Black	3.12	2.97	4.69	0.34	862.00	270.00	908.00	0.07	-39.55	-0.097	—
8.	Dhulia														
	Aner Dam	Compact basalt	Aphanitic	Greyish black	2.80	—	—	4.00	544.00	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	2.76	—	—	2.30	1433.00	—	—	—	—	—	—
	do	do	do	do	2.70	—	—	2.73	557.00	—	—	—	—	—	—
	do	do	do	do	2.80	—	—	2.00	971.00	—	—	—	—	—	—
9.	Jalgaon														
	Jalgaon	Compact basalt	Aphanitic	Greyish black	2.86	—	—	0.38	1001.00	—	—	—	—	—	—
	do	do	do	do	2.72	—	—	2.93	718.00	—	—	—	—	—	—
	do	do	do	do	2.92	—	—	0.24	2092.00	—	—	—	—	—	—
	Tapi Quarry	do	do	do	2.94	—	—	0.99	898.00	—	—	—	—	—	—
	do	do	do	do	2.96	—	—	2.17	396.00	—	—	—	—	—	—
	do	do	do	do	2.80	—	—	3.06	572.00	—	—	—	—	—	—
	do	do	do	do	—	—	—	0.99	—	—	—	—	—	—	—
	do	do	do	do	—	—	—	2.17	—	—	—	—	—	—	—
	do	Massive basalt	do	do	—	—	—	2.63	—	—	—	—	—	—	—
	Tapti Quarry	Compact basalt	Aphanitic	do	2.80	—	—	2.63	523.00	—	—	—	—	—	—
	Asara Quarry	do	do	do	2.98	—	—	1.60	2318.00	—	—	—	—	—	—
	Meharun Quarry	do	do	do	—	—	—	0.73	2543.00	—	—	—	—	—	—
	do	Deccan trap	Fine grained compact basalt	Dark grey	2.94	2.92	0.54	0.24	2092.00	—	—	0.89	+65.48	-0.063	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

Sl. No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS: 1125-1974¶)		REMARKS
			Structure and Texture (IS: 1123-1975*)	Colour (IS: 1123-1975*)	True Specific Gravity (IS: 1122-1974†)	Apparent Specific Gravity (IS: 1124-1974‡)	Porosity, Percent (IS: 1124-1974‡)	Water Absorption, Percent (IS: 1124-1974‡)	Compressive Strength kg/cm ² (IS: 1121-1974§)	Transverse Strength kg/cm ² (IS: 1121-1974§)	Shear Strength kg/cm ² (IS: 1121-1974§)	Durability, Percent Loss (IS: 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
	Hatnur Dam Dn.	Compact basalt	Aphanitic	Greyish black	2.85	—	—	0.86	1432.00	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	2.70	—	—	3.43	411.00	—	—	—	—	—	—
	Sakegaon Quarry	Compact basalt	Aphanitic	do	2.85	—	—	2.67	460.00	—	—	—	—	—	—
	do	do	do	do	—	—	—	2.67	—	—	—	—	—	—	—
	Kandari Quarry	do	do	do	—	—	—	2.63	—	—	—	—	—	—	—
	do	do	do	do	2.73	—	—	2.63	393.00	—	—	—	—	—	—
	Bharana Quarry	do	do	do	—	—	—	2.93	—	—	—	—	—	—	—
	Derabardi Quarry	Deccan trap	Medium grained basalt	Greenish grey	3.31	2.86	13.56	0.38	1001.00	—	—	0.46	+13.31	Nil	—
	Takarkheda	Deccan trap	Medium grained slightly weathered basalt	Light grey	3.23	2.72	15.73	2.93	718.00	—	—	0.57	+4.61	-0.131	Surface became rough after durability test
10. Nasik															
	Karanjwan Dam Foundation	Compact basalt	Aphanitic	Greyish black	2.61	—	—	0.85	208.00	—	—	—	—	—	—
	do	do	do	do	2.62	—	—	1.00	355.00	—	—	—	—	—	—
	Karanjwan Dam Dn. Foundation of Dam	Zeolitic basalt	Amygdaloidal	do	2.68	—	—	1.46	236.00	—	—	—	—	—	—
	do	do	do	do	2.65	—	—	2.50	208.00	—	—	—	—	—	—
	do	do	do	do	2.74	—	—	0.84	301.00	—	—	—	—	—	—
	do	do	do	do	—	—	—	1.46	—	—	—	—	—	—	—
	do	Compact basalt	Aphanitic	do	—	—	—	1.00	—	—	—	—	—	—	—
	Palkhed Canal Dn. Weir Site	do	do	do	2.90	—	—	0.62	1923.00	—	—	—	—	—	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

Sl. No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974†)	Porosity, Percent (IS : 1124-1974†)	Water Absorption, Percent (IS : 1124-1974†)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability, Percent Loss (IS : 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
	Manmad Lasalgaon Road	Compact basalt	Aphanitic	Greyish black	2.88	—	—	1.63	673.00	—	—	—	—	—	—
	Dabhadi	do	do	do	2.87	—	—	0.96	2005.00	—	—	—	—	—	—
	Burai River Bridge Village Chimthan	do	do	do	2.73	—	—	2.49	684.00	—	—	—	—	—	—
	do	do	do	do	2.90	—	—	2.07	1313.00	—	—	—	—	—	—
	Nandgaon Quarry	do	do	do	2.80	—	—	1.67	1615.00	—	—	—	—	—	—
	do	do	do	do	2.90	—	—	0.32	2694.00	—	—	—	—	—	—
	Vaitarna Masonry Dam Dn. Dam Foundation	do	do	do	2.76	—	—	1.10	1496.00	—	—	—	—	—	—
	do	do	do	do	2.76	—	—	2.20	841.00	—	—	—	—	—	—
	do	do	do	do	2.75	—	—	2.00	680.00	—	—	—	—	—	—
	Chankapur Quarries	Zeolitic basalt	Amygdaloidal	do	2.74	—	—	2.64	597.00	—	—	—	—	—	—
	do	do	do	do	2.73	—	—	1.15	968.00	—	—	—	—	—	—
	do	do	do	do	—	—	—	2.64	—	—	—	—	—	—	—
	do	do	do	do	—	—	—	1.15	—	—	—	—	—	—	—
	Spillway Quarry	do	do	do	2.56	—	—	3.68	509.00	—	—	—	—	—	—
	do	do	do	do	2.7	—	—	1.06	408.00	—	—	—	—	—	—
	Indhwani Quarry	do	do	do	2.80	—	—	1.65	822.00	—	—	—	—	—	—
	do	do	do	do	2.83	—	—	1.18	658.00	—	—	—	—	—	—
	do	do	do	do	2.96	—	—	0.96	658.00	—	—	—	—	—	—
	Mahadevi Quarry	do	do	do	2.81	—	—	2.07	936.00	—	—	—	—	—	—
	do	do	do	do	2.83	—	—	1.83	635.00	—	—	—	—	—	—
	Nasik	do	do	do	2.64	—	—	0.33	831.00	—	—	—	—	—	—
	Special Project Dn. Foundation of Dam	do	do	do	2.65	—	—	2.34	746.00	—	—	—	—	—	—
	Dabhadi	Compact basalt	Aphanitic	do	—	—	—	0.96	—	—	—	—	—	—	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

Sl. No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974‡)	Porosity, Percent (IS : 1124-1974‡)	Water Absorption, Percent (IS : 1124-1974‡)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability, Percent Loss (IS : 1126-1974¶)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
11. Osmanabad															
	Osmanabad	Compact basalt	Aphanitic	Greyish black	2.96	—	—	0.23	2814.00	—	—	—	—	—	—
	do	do	do	do	2.93	—	—	0.22	1346.00	—	—	—	—	—	—
	do	do	do	do	2.90	—	—	0.46	989.00	—	—	—	—	—	—
	do	do	do	do	2.95	—	—	0.50	665.00	—	—	—	—	—	—
	do	Deccan trap	Fine grained basalt	Black	3.01	2.95	1.96	0.50	665.00	195.00	561.00	0.34	-34.43	-0.124	—
	Latur Quarry	do	Medium grained compact basalt	Greenish grey	3.01	2.93	2.56	0.22	1346.00	103.00	527.00	0.34	+76.26	-0.128	—
	Udgir Quarry	Silicious rock	Fine grained compact basalt	Dark grey	2.97	2.90	2.29	0.46	989.00	319.00	750.00	0.41	+2.35	+0.212	—
12. Parbhani															
	Gohan Quarry	Deccan trap	Medium grained compact basalt	Dark grey	2.93	2.71	7.44	1.27	808.00	142.00	205.00	4.56	-23.52	-0.097	Cores scaled-out a thin layer of the thickness of 0.05" after durability test
13. Pune															
	Poona	Compact basalt	Aphanitic	Greyish black	2.97	—	—	1.40	521.00	—	—	—	—	—	—
14. Ratnagiri															
	Ratnagiri	do	do	do	2.90	—	—	0.52	1592.00	—	—	—	—	—	—
	do	Deccan trap	Medium grained compact basalt	Light grey	2.95	2.90	1.73	0.52	1592.00	283.00	512.00	0.80	+10.90	-0.61	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

SL No.	NAME OF PLACE	ROCK TYPE	PHYSICAL PROPERTIES										WEATHERING (IS: 1125-1974¶)		REMARKS
			Structure and Texture (IS: 1123-1975*)	Colour (IS: 1123-1975*)	True Specific Gravity (IS: 1122-1974†)	Apparent Specific Gravity (IS: 1124-1974†)	Porosity, Percent (IS: 1124-1974†)	Water Absorption, Percent (IS: 1124-1974†)	Compressive Strength kg/cm ² (IS: 1124-1974§)	Transverse Strength kg/cm ² (IS: 1121-1974§)	Shear Strength kg/cm ² (IS: 1121-1974§)	Durability, Percent Loss (IS: 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
15.	Sangali														
	Sangali	Compact basalt	Aphanitic	Greyish black	2.90	—	—	0.51	1238.00	—	—	—	—	—	—
	do	do	do	do	2.89	—	—	0.55	1378.00	—	—	—	—	—	—
	do	do	do	do	2.85	—	—	0.76	1271.00	—	—	—	—	—	—
	do	do	do	do	2.91	—	—	0.36	1165.00	—	—	—	—	—	—
	do	Zeolitic basalt	Amygdaloidal	do	2.91	—	—	0.46	1296.00	—	—	—	—	—	—
	Birnal Quarry	Deccan trap	Fine grained amygdaloidal basalt	Grey	3.08	2.91	5.81	0.46	1296.00	237.00	826.00	0.09	—38.11	—0.364	—
	Pavi Quarry	do	Fine grained basalt	Black	3.02	2.90	4.12	0.56	1238.00	194.00	484.00	0.25	—48.44	—0.450	—
	Siddhewadi	do	do	do	3.03	2.91	4.40	0.36	1165.00	187.00	378.00	0.42	—26.02	—0.272	—
	Talichi Quarry	do	do	Grey	3.02	2.89	4.64	0.55	1378.00	212.00	507.00	0.19	—45.49	—0.885	—
	Tasgaon	do	Fine grained porphyritic basalt	Black	3.03	2.85	6.29	0.76	1271.00	187.00	481.00	0.29	—34.51	—0.519	—
16.	Satara														
	Satara	Zeolitic basalt	Amygdaloidal	Greyish black	2.91	—	—	0.41	1214.00	—	—	—	—	—	—
	do	Deccan trap	Fine grained amygdaloidal basalt	Black	3.06	2.91	5.09	0.60	916.00	163.00	502.00	0.11	—15.05	—0.23	—
17.	Sholapur														
	Sholapur	do	do	do	3.07	2.96	3.52	0.41	1214.00	1224.00	631.00	0.46	+7.29	—0.054	—
	do	Zeolitic basalt	Amygdaloidal	Greyish black	2.96	—	—	0.41	1214.00	—	—	—	—	—	—
	Ujjani Quarry	Compact basalt	Aphanitic	do	2.89	—	—	0.87	1833.00	—	—	—	—	—	—
	do	do	do	do	3.00	—	—	1.40	1608.00	—	—	—	—	—	—
	do	do	do	do	2.87	—	—	0.96	1571.00	—	—	—	—	—	—

(Continued)

TABLE 1 TEST RESULTS OF BUILDING STONES IN MAHARASHTRA STATE — Contd

Sl. No.	NAME OF PLACE	Rock Type	PHYSICAL PROPERTIES										WEATHERING (IS : 1125-1974¶)		REMARKS
			Structure and Texture (IS : 1123-1975*)	Colour (IS : 1123-1975*)	True Specific Gravity (IS : 1122-1974†)	Apparent Specific Gravity (IS : 1124-1974†)	Porosity Percent (IS : 1124-1974†)	Water Absorption, Percent (IS : 1124-1974†)	Compressive Strength kg/cm ² (IS : 1121-1974§)	Transverse Strength kg/cm ² (IS : 1121-1974§)	Shear Strength kg/cm ² (IS : 1121-1974§)	Durability Percent Loss (IS : 1126-1974)	Change in Absorption, Percent	Change in Volume, Percent	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
18.	Thane														
	Bhatasa Quarry	Compact basalt	Aphanitic	Greyish black	2.77	—	—	2.93	501.00	—	—	—	—	—	—
	Haldapada Quarry	do	do	do	2.70	—	—	0.71	1691.00	—	—	—	—	—	—
	Warwada Quarry	do	do	do	2.75	—	—	0.33	2749.00	—	—	—	—	—	—
	Udhawa Quarry	do	do	do	2.70	—	—	0.62	2075.00	—	—	—	—	—	—
	Talasari Quarry	do	do	do	2.75	—	—	0.31	1664.00	—	—	—	—	—	—
	Dairy Project Dapchary	do	do	do	2.99	—	—	1.60	1656.00	—	—	—	—	—	—
19.	Wardha														
	Wardha	do	do	do	2.95	—	—	0.10	2568.00	—	—	—	—	—	—
	Wardha	do	do	do	2.95	—	—	0.14	2773.00	—	—	—	—	—	—
	Bhoskhuri Quarry	Deccan trap	Fine grained compact basalt	Dark grey	3.01	2.96	1.73	0.10	2568.00	335.00	866.00	0.41	+165.8	+0.0003	—
	Yelikeli quarry	do	do	do	2.97	2.95	0.81	0.14	2773.00	—	—	0.67	+122.4	—0.152	—
20.	Yeotmal														
	Yeotmal	Compact basalt	Aphanitic	Greyish black	2.91	—	—	0.68	2609.00	—	—	—	—	—	—
	Monegaon Quarry	Deccan trap	Fine grained compact basalt	Grey	2.91	2.87	1.10	0.66	2073.00	215.00	639.00	0.46	—39.8	—0.319	—
	Umarkhed Quarry	do	do	Dark grey	2.96	2.91	1.46	0.68	2609.00	—	—	0.58	—28.17	—0.126	—
	Woni Quarry	Sand stone	Medium grained sand stone	Brownish yellow	2.66	2.21	16.82	5.58	468.00	38.00	—	14.02	+9.88	—0.033	Cores were cracked after durability test

*Method of identification of natural building stones (first revision).

†Methods of test for determination of true specific gravity of natural building stones (first revision).

‡Method of test for determination of water absorption, apparent specific gravity and porosity of natural building stones (first revision).

§Methods of test for determination of strength properties of natural building stones (Parts I to IV).

||Method of test for determination of durability of natural building stones (first revision).

¶Method of test for determination of weathering of natural building stones (first revision).

INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

Base Units

Quantity	Unit	Symbol
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

Quantity	Unit	Symbol
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

Quantity	Unit	Symbol	Definition
Force	newton	N	1 N = 1 kg. m/s ²
Energy	joule	J	1 J = 1 N.m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V.s
Flux density	tesla	T	1 T = 1 Wb/m ²
Frequency	hertz	Hz	1 Hz = 1 c/s (s ⁻¹)
Electric conductance	siemens	S	1 S = 1 A/V
Electromotive force	volt	V	1 V = 1 W/A
Pressure, stress	pascal	Pa	1 Pa = 1 N/m ²

INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 27 01 31, 26 60 21

Telegrams : Manaksanstha

Regional Offices :

Western : Novelty Chambers, Grant Road
 Eastern : 5 Chowringhee Approach
 Southern : C.I.T. Campus, Adyar

	Telephone
BOMBAY 400007	37 97 29
CALCUTTA 700072	23-08 02
MADRAS 600020	41 24 42

Branch Offices :

'Pushpak', Nurmohamed Shaikh Marg, Khanpur
 'F' Block, Unity Bldg, Narasimharaja Square
 Gangotri Complex, Bhadbhada Road, T.T. Nagar
 22E Kalpana Area
 Ahimsa Bldg, SCO 82-83, Sector 17C
 9-8-56/57 L. N. Gupta Marg
 D-277 Todermal Marg, Banipark
 117/418 B Sarvodaya Nagar
 Patliputra Industrial Estate
 Hantex Bldg (2nd Floor), Rly Station Road

AHMADABAD 380001	2 03 91
BANGALORE 560002	2 76 49
BHOPAL 462003	6 27 16
BHUBANESHWAR 751014	5 36 27
CHANDIGARH 160071	2 83 20
HYDERABAD 500001	22 10 83
JAIPUR 302006	6 98 32
KANPUR 208005	8 12 72
PATNA 800013	6 28 08
TRIVANDRUM 695001	32 27