

X

इंटरनेट

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

"जानने का अधिकार, जीने का अधिकार" Mazdoor Kisan Shakti Sangathan "The Right to Information, The Right to Live"

"पुराने को छोड नये के तरफ" Jawaharlal Nehru "Step Out From the Old to the New"

मानक

IS 10810-28 (1984): Methods of test for cables, Part 28: Water absorption test (Electrical) [ETD 9: Power Cables]



6111111

Made Available By Public.Resource.Org



"ज्ञान से एक नये भारत का निर्माण″ Satyanarayan Gangaram Pitroda "Invent a New India Using Knowledge"

"ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता Bhartrhari-Nītiśatakam "Knowledge is such a treasure which cannot be stolen"





BLANK PAGE



PROTECTED BY COPYRIGHT

Indian Standard

METHODS OF TEST FOR CABLES

PART 28 WATER ABSORPTION TEST (ELECTRICAL)

1. Scope — Covers a method for measurement of water absorption by elastomeric insulation of electric cables.

2. Significance — Whenever the insulated cores are exposed to water/moisture, there is possibility of absorbing of the same by the insulants thereby deteriorating the electrical parameters. The degree of water absorbed will depend on the quantity as well as the quality of the various ingredients used for compounding of elastomers. Water absorption tests will indicate the quality of the compound used and also its suitability for critical application areas.

3. Terminology — When insulated cores are kept immersed in water, the capacitance values of the same are changed due to absorption of water. The degrees of water absorption is measured by recording the increase in capacitance from 1 to 14 days and from 7 to 14 days which are expressed as percentage of the one day and the seven days values respectively.

4. Apparatus

4.1 Water Tank — with heating arrangement.

4.2 Suitable Bridge — for measurement of capacitance.

4.3 High Voltage Source — 50 Hz.

4.4 Insulated Mats

5. Material - Water.

6. Test Specimen — A sample of the core about 5 m long is taken after vulcanization, but before the application of any covering except tape applied before vulcanization. Wherever possible, such tape is removed before the test.

7. Conditioning — The test specimen is prepared from the sample not less than 48 h after vulcanization by drying it for 24 \pm 1 h in air at 70 \pm 5°C. The specimen is allowed to cool to 50 \pm 2°C before immersion in water.

8. Procedure

8.1 The test specimen is accommodated in a water tank so that its middle portion for a length of 3 m is immersed whilst the ends are above the water level, each for a length of 0.75 m. Tap water is used, the temperature of which is maintained at $50 \pm 2^{\circ}$ C for 14 days. A tightly fitting cover is placed directly above the water surface with suitable water tight bushings for the ends of the specimen. The water level is kept constant.

8.2 The test is carried out with the average stress as specified in individual specification.

8.3 The capacitance is measured after 1, 7 and 14 days' continuous immersion, with the water at same temperature for all measurements.

9. Tabulation of Observations

Sample No.	No. of days	Water Temperature	Testing Stress	Capacitance μF		
		°C	V/mm	1 Day	7 Days	14 Days

NEW DELHI 110002

IS: 10810 (Part 28) - 1984

10. Calculation

10.1 Percentage increase in capacitance for

1 to 14 days =
$$\frac{C_{14} - C_1}{C_1} \times 100$$

Percentage increase in capacitance for

7 to 14 days =
$$\frac{C_{14} - C_7}{C_7} \times 100$$

where

 C_1 = the capacitance value after 1 day (after 24 h)

 C_7 = the capacitance value after 7 days (after 168 h)

 C_{14} = the capacitance value after 14 days (after 336 h)

11. Report

11.1 Water Absorption Test of Elastomeric Insulation

Cable Type

Batch No./Lot No.

Cable No./Drum No.

Date of Testing

11.2 Results

Reference specification___

		e m Supachance		
1 to 14 days		7 to 14 days		
Observed	Specified	Observed	Specified	
	0bserved	1 to 14 days Observed Specified	1 to 14 days 7 to 14 Observed Specified Observed	

11.3 Conclusion — The specimen meets/does not meet the requirements of the specification.