

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 228-18 (1998): Methods of chemical analysis of steels, Part 18: Determination of oxygen by instrumental method [MTD 16: Alloy Steels and Forgings]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



भारतीय मानक

इस्पात के रासायनिक विश्लेषण की प्रणाली

भाग 18 मापयन्त्री प्रणाली द्वारा आक्सीजन का निर्धारण
(0.001 से 0.100 0 प्रतिशत आक्सीजन के लिए)

(दूसरा पुनरीक्षण)

Indian Standard

**METHODS OF CHEMICAL ANALYSIS
OF STEELS**

**PART 18 DETERMINATION OF OXYGEN BY INSTRUMENTAL METHOD
(FOR OXYGEN 0.001 to 0.100 0 PERCENT)**

(*Second Revision*)

ICS 77.080.20

© BIS 1998

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

FOREWORD

This Indian Standard (Part 18) (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Methods of Chemical Analysis of Ferrous Metals Sectional Committee had been approved by the Metallurgical Engineering Division Council.

IS 228, which was first published in 1952 and subsequently revised in 1959, covered the chemical analysis of plain carbon and low alloy steels, along with pig iron and cast iron. It was revised again to make it comprehensive in respect of steel analysis and to exclude pig iron and cast iron which were being covered in separate standards. During its second revision the standard has been split up in several parts.

This part covers the methods for determination of oxygen. The other parts of this series are:

IS 228	Methods for chemical analysis of steels :
(Part 1) : 1987	Determination of carbon by volumetric method (for carbon 0.05 to 2.50 percent)
(Part 2) : 1987	Determination of manganese in plain carbon and low alloy steels by arsenite method
(Part 3) : 1987	Determination of phosphorus by alkalimetric method
(Part 4) : 1987	Determination of total carbon by gravimetric method (for carbon greater than or equal to 0.1 percent)
(Part 5) : 1987	Determination of nickel by dimethyl glyoxime (gravimetric) method (for nickel greater than or equal to 0.1 percent)
(Part 6) : 1987	Determination of chromium by persulphate oxidation method (for chromium greater than or equal to 0.1 percent)
(Part 7) : 1990	Determination of molybdenum by benzoinoxine method (for molybdenum greater than or equal to 1 percent)
(Part 8) : 1989	Determination of silicon by the gravimetric method (for silicon 0.05 to 5.00 percent)
(Part 9) : 1989	Determination of sulphur in plain carbon steels by evolution method (for sulphur 0.01 to 0.25 percent)
(Part 10) : 1989	Determination of molybdenum by thiocyanate (photometric) method in low and high alloy steels (for molybdenum 0.01 to 1.5 percent)
(Part 11) : 1990	Determination of silicon by photometric method in carbon steels and low alloy steels (for silicon 0.01 to 0.05 percent)
(Part 12) : 1988	Determination of manganese by periodate spectrophotometric method in low and high alloy steels (for manganese 0.01 to 2.0 percent)
(Part 13) : 1982	Determination of arsenic
(Part 14) : 1988	Determination of carbon by thermal conductivity method (for copper 0.005 to 2.000 percent)
(Part 15) : 1992	Determination of copper by thiosulphate iodide method (for copper 0.05 to 5 percent)
(Part 16) : 1992	Determination of tungsten by spectrophotometric method (for tungsten 0.1 to 2 percent)
(Part 17) : 1998	Determination of nitrogen by thermal conductivity method (for nitrogen up to .04 percent)

In this revision 'Instrumental Method' for determination of oxygen in steel has been introduced.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be same as that of the specified value in this standard.

*Indian Standard***METHODS OF CHEMICAL ANALYSIS
OF STEELS****PART 18 DETERMINATION OF OXYGEN BY INSTRUMENTAL METHOD
(FOR OXYGEN 0.001 to 0.100 0 PERCENT)***(Second Revision)***1 SCOPE**

This standard (Part 18) describes the method for determination of oxygen in steel in the range from 0.001 to 0.100 0 percent by available instruments.

2 SAMPLING

2.1 Location and selection of sample can be as per requirements and to get a good representative sample. Use only solid samples to minimise the errors due to surface oxidation. Sample size and weight shall be such so as to suit the crucible in which fusion is being carried out.

2.2 Sample preparation technique is critical to attain consistent, reliable and reproducible oxygen readings. Cut samples to the appropriate size using cut-off wheels or by machining. Avoid over heating and other oxide contaminations during preparation. Typical sample size of 5-6 mm dia (or 5 mm²) and 50 mm length is suitable for all types of instruments. File the piece with clean, smooth file and abrade the entire surface to remove all traces of oxidation. Cut by using clean hacksaw blade (without paint) to 3-4 mm long pieces weighing approx 1 g. Hand file again the cut faces. With a fine grade silicon carbide paper clean the surface and drop it in a bottle containing acetone and do ultrasonic cleaning. While handling the sample use tweezers. Do not touch the surface with fingers during and in the following stages of cleaning.

3 DETERMINATION OF OXYGEN**3.1 Outline of the Method**

The sample is melted in a graphite crucible under inert gas stream, at a temperature of not less than 2 000°C to release oxygen, which combines with carbon from the crucible to form carbon monoxide and which is carried along with the inert gas to infrared detector. The detector output is displayed as oxygen content. The detector output is calibrated with similar standards for which certified oxygen values are available.

3.2 Instruments

3.2.1 For the instruments based on the infrared detector the sample is melted in the furnace in a stream

of argon helium or nitrogen depending upon the instrument model and the evolved gases are passed through infrared detector where CO is measured directly or after its conversion to CO₂. The detector response to this change is displayed directly as oxygen content.

3.3 Reagents

3.3.1 *Acetone or n-Hexane*

3.3.2 *Ascarite*

3.3.3 *Inert Gas Helium, Argon of the Required Purity*

3.3.4 *Magnesium Perchlorate*

3.3.5 *Charcoal and Copper Oxide, in a rare-earth oxide mixed based (used in some instruments).*

3.4 Procedure

3.4.1 Prepare and stabilise the instrument. Change the chemicals and filters as required. Check for leakage and run two or three dummy analysis to check the operation and clean the system before taking up calibration with standard samples.

3.4.2 Since accuracy of analysis mainly depends on the standards, for calibration select highly homogeneous samples of identical base material, for which oxygen values have been certified. In some instruments, gas dosing calibration is available to set up the instrument response, but it is recommended to confirm the same with standards.

3.4.3 Determine the blank value as per the instructions and incorporate the same if the instrument is automatic-type or it can be reduced from the oxygen value later.

3.4.4 Weigh accurately to the nearest 1 mg of calibration standard having low, medium and high oxygen contents. Weight shall be as per the instrument's capability.

3.4.5 Follow the calibration procedures as laid down by the operation manual of the instrument and

establish the instrument response. Confirm the same by running two additional standards. The response should be within ± 0.0005 percent oxygen for duplicate runs.

3.4.6 Take freshly prepared sample as per the Sample preparation procedure (or sample prepared and stored in acetone). Wash the same in acetone or n-hexane and dry thoroughly. Weigh the sample accurately and place it in the automatic sample loading device. Carry

out analysis as per the procedure specified by the instrument manufacturer. Note the oxygen value. Carry out the analysis in replicate and average the values, discarding the outlier beyond ± 0.0005 percent. At least three values should be within ± 0.0005 percent.

3.5 Precision

Expected ± 0.0005 at 0.0050 percent oxygen level.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'

This Indian Standard has been developed from Doc: No. MTD 2 (4105).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 323 01 31, 323 33 75, 323 94 02

Telegrams: Manaksanstha
(Common to all offices)

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

Telephone

323 76 17, 323 38 41

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola
CALCUTTA 700054

{ 337 84 99, 337 85 61
337 86 26, 337 91 20

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43
60 20 25

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42
235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
MUMBAI 400093

{ 832 92 95, 832 78 58
832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI.
HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR.
PATNA. PUNE. THIRUVANANTHAPURAM.