

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 7280 (1974): Bare wire electrodes for submerged arc welding of structural steels [MTD 11: Welding General]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 7280 - 1974
(Reaffirmed 1997)

Indian Standard

**SPECIFICATION FOR
BARE WIRE ELECTRODES FOR SUBMERGED
ARC WELDING OF STRUCTURAL STEELS**

(Fourth Reprint MAY 2000)

UDC 621.791.753.5.042:624.014.25

© Copyright 1974

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

AMENDMENT NO. 1 JULY 2008
TO
IS 7280 : 1974 SPECIFICATION FOR BARE
WIRE ELECTRODES FOR SUBMERGED ARC
WELDING OF STRUCTURAL STEELS

(Page 5, clause 7.1) — Add the following matter at the end of the last sentence:

'and shall be calculated as per method given in 7.2'.

(Page 5, clause 7.1) — Insert the following new clauses at the end:

7.2 Method for Determination of Copper Content in Coated Wire

7.2.1 Procedure

7.2.1.1 Take about 50 cm of copper coated wire from coil and weigh (W_1).

7.2.1.2 The wire shall be kept in 25 percent ammonia solution for about 10-12 h. Reaction may be accelerated and completed within 1 h by addition of 1-3 cc of hydrogen peroxide.

7.2.1.3 After all the copper is dissolved the wire shall be removed from ammonia solution, washed with distilled water and alcohol, dried and weighed (W_2).

7.2.1.4 Percentage of copper =
$$\frac{(W_1 - W_2)}{W_1} \times 100$$

where

W_1 = initial weight of copper coated wire in g; and

W_2 = final weight of wire in g.

Indian Standard

SPECIFICATION FOR BARE WIRE ELECTRODES FOR SUBMERGED ARC WELDING OF STRUCTURAL STEELS

Welding General Sectional Committee, SMDC 14

<i>Chairman</i>	<i>Representing</i>
SHRI R. GHOSH	Indian Oxygen Limited, Calcutta
<i>Members</i>	
SHRI J. K. AHLUWALIA	Stewarts & Lloyds of India Ltd, Calcutta
SHRI M. M. GHOSH (<i>Alternate</i>)	
SHRI N. C. BAGCHI	National Test House, Calcutta
SHRI B. C. BISWAS (<i>Alternate</i>)	
SHRI S. BALASUBRAHMANYAM	Binny Ltd, Madras
SHRI K. BALMANOHAR	Hindustan Shipyard Ltd, Visakhapatnam
SHRI R. N. CHAKRABORTY	Braithwaite & Co (India) Ltd, Calcutta
SHRI B. N. DAS	National Metallurgical Laboratory (CSIR), Jamshedpur
SHRI S. P. DASGUPTA	Central Mechanical Engineering Research Institute (CSIR), Durgapur
SHRI B. SEN (<i>Alternate</i>)	
DIRECTOR, RESEARCH AND DESIGN, B & R BRANCH, CHANDIGARH	Public Works Department, Government of Haryana, Chandigarh
EXECUTIVE ENGINEER (ELECTRI- CAL), ELECTRICAL DIVISION No. 1, NEW DELHI	Central Public Works Department, New Delhi
EXECUTIVE ENGINEER (ELECTRI- CAL), CENTRAL ELECTRICAL DIVISION No. 1, CALCUTTA (<i>Alternate</i>)	
SHRI H. D. GOVINDARAJ	Philips India Ltd, Bombay
DR J. VAID (<i>Alternate</i>)	
SHRI S. K. HARI	Malik Electricals Pvt Ltd, Bombay
SHRI M. K. SINHA (<i>Alternate</i>)	
DR J. JAIN	Tata Engineering and Locomotive Co Ltd, Jamshedpur
PROF A. P. JAMBULINGAM	Indian Society for Technical Education, New Delhi

(Continued on page 2)

© Copyright 1974

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 7280 - 1974

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
JOINT DIRECTOR (M & C), RDSO, LUCKNOW	Ministry of Railways
CHEMIST AND METALLURGIST, INTEGRAL COACH FACTORY, PERAMBUR (Alternate I)	
PRODUCTION ENGINEER (SHELL), INTEGRAL COACH FACTORY, PERAMBUR (Alternate II)	
SHRI M. V. D. KAMATH	Indian Engineering Association, Calcutta
SHRI M. T. KANBE	Directorate General of Supplies & Disposals (Inspection Wing), New Delhi
SHRI S. N. BASU (Alternate)	
SHRI G. S. KODIKAL	Bharat Heavy Plate & Vessels Ltd, Visakhapatnam
SHRI A. P. SANYAL (Alternate)	
SHRI S. V. NADKARNI	Advani-Oerlikon Private Ltd, Bombay
SHRI P. S. VISWANATH (Alternate)	
SHRI A. C. MUKHERJEE	Power Cables Pvt Ltd, Bombay
SHRI J. R. PRASHER	Bharat Heavy Electricals Ltd, Hardwar
SHRI K. M. POLE	Walchandnagar Industries, Walchandnagar
SHRI G. D. APTE (Alternate)	
SHRI H. L. PRABHAKAR	Larsen & Toubro Ltd, Bombay
SHRI S. S. RAGHAVAN	Engineer-in-Chief's Branch, Army Headquarters
SHRI K. S. HANS (Alternate)	
SHRI P. B. RAO	Ministry of Defence (DGI)
SHRI S. C. ROY	Central Boilers Board, New Delhi
SHRI V. V. SATHYANARAYANA	Mining & Allied Machinery Corpn, Durgapur
SHRI S. K. BANERJIA (Alternate)	
SHRI S. K. SENGUPTA	Hindustan Steel Ltd, Ranchi
SHRI V. V. KAVISWAR (Alternate)	
SHRI H. K. SHARMA	Directorate General of Technical Development, New Delhi
SHRI K. C. SHARMA (Alternate)	
SHRI A. SRINIVASALU	Bharat Heavy Electricals Ltd, Tiruchirappalli
SHRI B. PATTABHIRAMAN (Alternate)	
SHRI R. K. SRIVASTAVA	Mukand Iron and Steel Works Ltd, Bombay
SHRI V. R. SUBRAMANIAN	Indian Oxygen Limited, Calcutta
SHRI J. C. ACHARYA (Alternate)	
SHRI S. SUNDARESAN	Directorate General of Employment and Training, New Delhi
SUPERINTENDING ENGINEER, CENTRAL MECHANICAL CIRCLE, MADRAS	Public Works Department, Government of Tamil Nadu, Madras
SHRI C. R. RAMA RAO, Director (Struc & Met)	Director General, ISI (Ex-officio Member)

Secretary

SHRI M. S. NAGARAJ

Deputy Director (Struc & Met), ISI

(Continued on page 9)

Indian Standard

SPECIFICATION FOR BARE WIRE ELECTRODES FOR SUBMERGED ARC WELDING OF STRUCTURAL STEELS

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 29 March 1974, after the draft finalized by the Welding General Sectional Committee had been approved by the Structural and Metals Division Council.

0.2 This standard is intended to serve as a guide for the manufacture and selection of bare wire electrodes for submerged arc welding of structural steels.

0.3 In the preparation of this standard due consideration has been given to the manufacturing and trade practices followed in the field in this country. Assistance has also been derived from Doc: IIS/IIW — 385-72 'Classification and symbolization of bare steel wire electrodes and fluxes for submerged arc welding of structural steels' issued by the Sub-Commission on Submerged Arc Welding of the International Institute of Welding.

0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements of solid filler wires for submerged arc welding of structural steels (28-50 kgf/mm² yield strength and 34-70 kgf/mm² ultimate tensile strength).

2. TERMINOLOGY

2.1 For the purpose of this standard the definitions given in IS : 812-1957† shall apply.

*Rules for rounding off numerical values (revised).

†Glossary of terms relating to welding and cutting of metals.

3. SUPPLY OF MATERIAL

3.1 General requirements relating to the supply of solid filler wires for submerged arc welding of structural steels shall be as laid down in IS : 1387-1967*.

4. DIMENSIONS AND TOLERANCES

4.1 The diameters of wires shall be as follows:

1.6, 2.0, 2.5, 3.15, 4.0, 5.0, 6.3 and 8.0 mm.

4.2 The tolerance on the diameters of wires shall be ± 0.05 mm.

5. REELS FOR WIRE

5.1 The dimensions of the rims and the coils on which wire may be supplied shall be as agreed to between the purchaser and the manufacturer and they shall conform to one of the appropriate dimensions and tolerances given in Tables 1 and 2.

TABLE 1 DIMENSIONS AND TOLERANCES FOR RIMS

INTERNAL DIAMETER mm	WIDTH mm	NET WEIGHT, <i>Max</i> kg
300 ± 5	100 ± 3	12.5 ± 1
300 ± 5	100 ± 3	25 ± 2
600 ± 5	100 ± 3	80 ± 5

TABLE 2 DIMENSIONS AND TOLERANCES FOR COILS

INTERNAL DIAMETER mm	NET WEIGHT, <i>Max</i> kg
300 ± 25	12.5 ± 1
300 ± 25	25 ± 2
600 ± 25	80 ± 5

6. REELING CONDITIONS

6.1 The wire shall be closely wound in layers on the rim in continuous length; it shall be free from kinks, waves, or sharp bends, and free to unwind without restriction. The adjacent windings within a layer may not necessarily be touching.

*General requirements for the supply of metallurgical materials (*first revision*).

6.2 Coils shall be properly bound to prevent entanglement of turns in normal handling and when used with tied start and finish ends. The finished end shall be clearly marked for identification. All coils shall contain continuous length of wire made from a single heat or lot.

6.3 Butt welds when present in the wire shall be suitably made so as not to interfere with the uniform uninterrupted feeding of the wire on automatic and semi-automatic equipment.

7. CONDITIONS OF WIRES

7.1 Filler wires shall have smooth finish and they shall be free from surface imperfections, corrosion products, grease, excessive oxide or other foreign matter which would affect adversely the properties of the weld or the operation of the welding equipment. Temper and surface conditions shall be suitable for uniform uninterrupted feeding on automatic or semi-automatic welding equipment. Unless otherwise specified the wires shall have a uniform, unbroken well-bonded and smooth copper coating applied onto the thoroughly cleaned wire surface. The copper content of the coated wire expressed as a percentage of the wire and the coating shall not exceed 0.4 percent by weight.

8. CLASSIFICATION

8.1 The filler wires shall be classified on the basis of their chemical composition.

8.2 In a classification, for example, 'AS-X' 'A' indicates that the wire is used for semi-automatic or automatic submerged arc welding and 'S' indicates solid bare wire. The digit 'X' used as a suffix is equal to twice the amount of the average manganese content of the wire. The presence of molybdenum, silicon, nickel, etc, is indicated by further suffixes like Mo, Si, Ni, etc.

The IS Classification 'AS-2 Mo' means that the solid wire is suitable for automatic and semi-automatic submerged arc welding and it contains 1 percent average content of manganese and an intentional addition of molybdenum.

9. CHEMICAL COMPOSITION

9.1 The chemical composition of filler wires, when analyzed in accordance with IS : 228-1959*, IS : 228 (Part I)-1972†, IS : 228 (Part II)-1972‡,

*Methods of chemical analysis of pig iron, cast iron and plain carbon and low-alloy steels (revised).

†Methods of chemical analysis of steels: Part I Determination of carbon by volumetric method (for carbon ≥ 0.1 percent) (second revision).

‡Methods of chemical analysis of steels: Part II Determination of manganese in plain carbon and low alloy steels by arsenite method (second revision).

TABLE 3 CHEMICAL COMPOSITION OF FILLER WIRES

(Clause 9.1)

IS CLASSIFICATION	CHEMICAL COMPOSITION, PERCENT						
	Carbon	Silicon	Manganese	Molybdenum	Nickel	Phosphorus <i>Max</i>	Sulphur <i>Max</i>
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
AS-1	0.10 (<i>Max</i>)	0.03 (<i>Max</i>)	0.40-0.60	—	—	0.03	0.03
AS-1 Si	0.08-0.15	0.10-0.40	0.40-0.60	—	—	0.03	0.03
AS-2	0.08-0.15	0.05-0.15	0.80-1.20	—	—	0.03	0.03
AS-2 Si	0.08-0.15	0.15-0.40	0.80-1.20	—	—	0.03	0.03
AS-2 Mo	0.08-0.15	0.05-0.15	0.80-1.20	0.45-0.60	—	0.03	0.03
AS-2 Ni	0.06-0.12	0.05-0.15	0.80-1.20	—	0.80-1.20	0.02	0.02
AS-3	0.08-0.15	0.05-0.25	1.30-1.70	—	—	0.03	0.03
AS-3 Mo	0.08-0.15	0.05-0.25	1.30-1.70	0.45-0.60	—	0.03	0.03
AS-3 Mo Ni	0.08-0.12	0.05-0.25	1.30-1.70	0.45-0.60	1.30-1.70	0.02	0.02
AS-4	0.08-0.16	0.05-0.25	1.80-2.20	—	—	0.03	0.03
AS-4 Mo	0.08-0.17	0.15-0.30	1.80-2.20	0.45-0.60	—	0.03	0.03
AS-6	0.08-0.17	0.20-0.30	2.80-3.20	—	—	0.03	0.03
AS-6 Mo	0.08-0.17	0.15-0.30	2.80-3.20	0.45-0.60	—	0.03	0.03

IS : 228 (Part III)-1972*, IS : 228 (Part IV)-1974†, IS : 228 (Part V)-1974‡, IS : 228 (Part VI)-1974§ and IS : 228 (Part VII)-1974||, shall be as given in Table 3. Where the wire is copper-coated, the analysis shall be made after the copper has been removed.

9.2 The manufacturer shall carry out the analysis from each cast of steel and, when required by the purchaser, supply a certified cast analysis of a sample of steel from each cast.

9.3 Regarding residual elements the acceptance limits shall be as agreed to between the manufacturer and the purchaser.

10. METHOD OF SAMPLING

10.1 The location and the method of sampling shall be as agreed to between the purchaser and the manufacturer.

10.2 The area to be sampled shall be obtained from the combined transverse sections by bundling the rods or wires after cutting into suitable lengths or by folding. The area shall be cleaned by grinding. The copper coating shall be removed to expose the base metal before grinding. The sample shall be collected by milling out the areas.

11. PACKING

11.1 Reels of wire shall be suitably packed to guard against atmospheric influence, damage, combination or deterioration during storage, transit and inspection.

11.2 If the condition of the wire is such that special protection during storage or special treatment before use is desirable, the manufacturer shall give details of such special protection or treatment on the package.

12. MARKING

12.1 Each reel or coil of wire shall be clearly marked with the following information:

- a) Classification coding,
- b) Name of manufacturer,

*Methods of chemical analysis of steels: Part III Determination of phosphorus by alkalimetric method (*second revision*).

†Methods of chemical analysis of steels: Part IV Determination of carbon (gravimetric method) for carbon ≥ 0.1 percent (*second revision*).

‡Methods of chemical analysis of steels: Part V Determination of nickel by dimethylglyoxime (gravimetric) method (for nickel ≥ 0.5 percent) (*second revision*).

§Methods of chemical analysis of steels: Part VI Determination of chromium by persulphate oxidation method (for chromium ≥ 0.5 percent) (*second revision*).

||Methods of chemical analysis of steels: Part VII Determination of molybdenum by alpha benzoinoxime method (for molybdenum above 1 percent) (*second revision*).

IS : 7280 - 1974

- c) Trade designation of wire,
- d) Wire size,
- e) Cast number, and
- f) Net weight of the reel/coil.

12.1.1 The product may also be marked with Standard mark.

12.1.2 The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Continued from page 2)

Subcommittee for Welding Consumables, SMDC 14 : 1

Convener

SHRI V. R. SUBRAMANIAN

Representing

Indian Oxygen Limited, Calcutta

Members

SHRI K. R. ANANT RAM

ACC-Vickers-Babcock Ltd, Durgapur

SHRI S. N. MUKHERJEE (Alternate)

DEPUTY DIRECTOR (Met-I), Ministry of Railways

RDSO, LUCKNOW

CHEMIST AND METALLURGIST,

ICF, PERAMBUR (Alternate)

SHRI R. KRISHNAMURTHI

Bharat Heavy Electricals Ltd, Tiruchirapalli

SHRI R. C. MENON

**Ministry of Defence (Department of Defence
Production)**

SHRI A. C. MUKHERJEE

Power Cables Pvt Ltd, Kalyan

SHRI S. V. NADKARNI

Advani-Oerlikon Private Ltd, Bombay

SHRI J. R. PRASHER

Bharat Heavy Electricals Ltd, Hardwar

IS : 7280 - 1974

- c) Trade designation of wire,
- d) Wire size,
- e) Cast number, and
- f) Net weight of the reel/coil.

12.1.1 The product may also be marked with Standard mark.

12.1.2 The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

(Continued from page 2)

Subcommittee for Welding Consumables, SMDC 14 : 1

Convener

SHRI V. R. SUBRAMANIAN

Representing

Indian Oxygen Limited, Calcutta

Members

SHRI K. R. ANANT RAM

ACC-Vickers-Babcock Ltd, Durgapur

SHRI S. N. MUKHERJEE (*Alternate*)

DEPUTY DIRECTOR (MET-I), Ministry of Railways

RDSO, LUCKNOW

CHEMIST AND METALLURGIST,

ICF, PERAMBUR (*Alternate*)

SHRI R. KRISHNAMURTHI

Bharat Heavy Electricals Ltd, Tiruchirapalli

SHRI R. C. MENON

Ministry of Defence (Department of Defence
Production)

SHRI A. C. MUKHERJEE

Power Cables Pvt Ltd, Kalyan

SHRI S. V. NADKARNI

Advani-Oerlikon Private Ltd, Bombay

SHRI J. R. PRASHER

Bharat Heavy Electricals Ltd, Hardwar

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 323 0131, 323 3375, 323 9402 Fax :+ 91 011 3234062, 3239399, 3239382

E - mail : bis@vsnl.com. Internet : <http://wwwdel.vsnl.net.in/bis.org>

Central Laboratory:

Plot No. 20/9, Site IV, Sahibabad Industrial Area, Sahibabad 201010

Telephone

77 00 32

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002 323 76 17

*Eastern : 1/14 CIT Scheme VII, V.I.P. Road, Kankurgachi, CALCUTTA 700054 337 86 62

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022 60 38 43

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113 235 23 15

†Western : Manakalaya, E9, MIDC, Behind Marol Telephone Exchange,
Andheri (East), MUMBAI 400093 832 92 95

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001 550 13 48

‡Peenya Industrial Area, 1st Stage, Bangalore-Tumkur Road,
BANGALORE 560058 839 49 55

Commercial-cum-Office Complex, Opp. Dushera Maidan, E-5 Arera Colony,
Bittan Market, BHOPAL 462018 72 34 52

62/63, Ganga Nagar, Unit VI, BHUBANESWAR 751001 40 36 27

Kalai Kathir Building, 670 Avinashi Road, COIMBATORE 641018 21 01 41

Plot No. 43, Sector 16 A, Mathura Road, FARIDABAD 121001 28 88 01

Savitri Complex, 116 G.T. Road, GHAZIABAD 201001 71 19 98

53/5 Ward No.29, R.G. Barua Road, 5th By-lane, GUWAHATI 781003 54 11 37

5-8-56C, L.N. Gupta Marg, Nampally Station Road, HYDERABAD 500001 320 10 84

E-52, Chitrangan Marg, C- Scheme, JAIPUR 302001 37 38 79

117/418 B, Sarvodaya Nagar, KANPUR 208005 21 68 76

Seth Bhawan, 2nd Floor, Behind Leela Cinema, Naval Kishore Road,
LUCKNOW 226001 21 89 23

NIT Building, Second Floor, Gokulpat Market, NAGPUR 440010 52 51 71

Patilputra Industrial Estate, PATNA 800013 26 28 08

Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005 32 36 35

'Sahajanand House' 3rd Floor, Bhaktinagar Circle, 80 Feet Road,
RAJKOT 360002 36 85 86

T.C. No. 14/1421, University P. O. Palayam, THIRUVANANTHAPURAM 695034 32 21 04

*Sales Office is at 5 Chowringhee Approach, P.O. Princep Street,
CALCUTTA 700072 27 10 85

†Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400007 309 65 28

‡Sales Office is at 'F' Block, Unity Building, Narashimaraja Square,
BANGALORE 560002 222 39 71