

# इंटरनेट

# मानक

## Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 3400-9 (2003): Methods of Test for Vulcanized Rubber,  
Part 9: Rubber, Vulcanized - Determination of Density [PCD  
13: Rubber and Rubber Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”



BLANK PAGE



भारतीय मानक  
वल्कनीकृत रबड़ की परीक्षण पद्धतियाँ  
भाग 9 रबड़ वल्कनीकृत — घनत्व ज्ञात करना  
( दूसरा पुनरीक्षण )

*Indian Standard*

**METHODS OF TEST FOR VULCANIZED RUBBER**

**PART 9 RUBBER, VULCANIZED — DETERMINATION OF DENSITY**

*( Second Revision )*

ICS 83.060

© BIS 2003

**BUREAU OF INDIAN STANDARDS**  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

## NATIONAL FOREWORD

This Indian Standard (Part 9) (Second Revision) which is identical with ISO 2781:1988 'Rubber, vulcanized — Determination of density' issued by the International Organization for Standardization (ISO) was adopted by the Bureau of Indian Standards on the recommendations of the Rubber and Rubber Products Sectional Committee and approval of the Petroleum, Coal and Related Products Division Council.

This standard was first published in 1967 aligning with ISO 2781:1975 'Determination of density of vulcanized rubbers' and revised in 1978. In the first revision, determination was made by observation of gravitational forces under different conditions, but for convenience, these forces were expressed in mass units. The Committee, therefore, decided to revise this standard to completely align with ISO 2781:1988.

The text of ISO Standard has been proposed to be approved as suitable for publication as Indian Standard without deviations. Certain conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear referring to this standard, they should be read as 'Indian Standard'.
- b) Comma (,) has been used as a decimal marker while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

For tropical countries like India, the standard temperature and the relative humidity shall be taken as  $27 \pm 2^{\circ}\text{C}$  and  $65 \pm 5$  percent respectively.

*Indian Standard*  
**METHODS OF TEST FOR VULCANIZED RUBBER**  
**PART 9 RUBBER, VULCANIZED—DETERMINATION OF DENSITY**  
*( Second Revision )*

## 1 Scope

This International Standard specifies two methods of test for the determination of the density of solid vulcanized rubber.

Such determinations are of importance in the control of the quality of a rubber compound and in the calculation of the mass of rubber required to produce a given volume of vulcanizate.

This International Standard does not cover the determination of the relative density of rubber, which is the ratio of the mass of a given volume of the rubber to the mass of an equal volume of pure water at a given temperature.

In this International Standard the determination is made by observation of gravitational forces under different conditions but, for convenience, these forces are expressed in mass units.

## 2 Definition

For the purposes of this International Standard, the following definition applies.

**density:** The mass of unit volume of the rubber at a stated temperature. It is expressed in megagrams per cubic metre ( $\text{Mg}/\text{m}^3$ ).

## 3 Principle

Two methods, A and B, are given.

In method A the masses of the test piece in air and in water are determined using an analytical balance equipped with a pan straddle. The mass when immersed in water is less than that in air by the mass of water displaced, the volume of water displaced being equal to that of the test piece.

Method B is intended to be used only when it is necessary to cut up the test piece into small pieces to eliminate air spaces, as in the case of narrow bore tubing and electric cable insulation. Measurements are made using a balance and a density bottle.

## 4 Apparatus

Ordinary laboratory apparatus and

**4.1 Analytical balance,** accurate to 1 mg.

**4.2 Balance pan straddle,** of convenient size to support the beaker and permit determination of the mass of the test piece in water (for method A).

**4.3 Beaker,** 250  $\text{cm}^3$  capacity (or smaller if necessitated by the design of the balance) (for method A).

**4.4 Density bottle** (for method B).

## 5 Test piece

**5.1** The test piece shall consist of a piece of the rubber with smooth surfaces, free from crevices and dust, and having a mass of at least 2,5 g. For method B the shape of the test piece shall be such as to permit cutting into suitable pieces (see 9.3).

**5.2** A minimum of two tests shall be made.

## 6 Time-interval between vulcanization and testing

Unless otherwise specified for technical reasons, the following requirements for time-intervals shall be observed.

**6.1** For all test purposes, the minimum time between vulcanization and testing shall be 16 h.

**6.2** For non-product tests, the maximum time between vulcanization and testing shall be 4 weeks and for evaluations

intended to be comparable, the tests, as far as possible, shall be carried out after the same time-interval.

**6.3** For product tests, whenever possible, the time between vulcanization and testing shall not exceed 3 months. In other cases, tests shall be made within 2 months of the date of receipt by the customer of the product.

## 7 Conditioning of test pieces

**7.1** Samples and test pieces shall be protected from direct sunlight during the interval between vulcanization and testing.

**7.2** Samples, after such preparation as is necessary, shall be conditioned at a standard temperature (that is,  $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ) for at least 3 h before the test pieces are cut. These test pieces may be tested immediately but, if not, they shall be kept at the standard temperature until tested. If the preparation involves buffing, the interval between buffing and testing shall not exceed 72 h.

## 8 Temperature of test

The test shall normally be carried out at a standard temperature ( $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ), the same temperature being used throughout one test or series of tests intended to be comparable.

## 9 Procedure

### 9.1 Preparation of sample

If fabric is attached to, or embedded in, the samples, it shall be removed before cutting the test pieces. The method of removal shall preferably avoid the use of a swelling liquid, but, if necessary, a suitable non-toxic liquid of low boiling point may be used to wet the contacting surfaces. Care shall be taken to avoid stretching the rubber during the separation from the fabric, and the liquid, if used, shall be allowed to evaporate completely from the rubber surfaces after separation. Cloth-marked surfaces shall be made smooth by buffing.

### 9.2 Method A

Suspend the test piece (clause 5) from the hook on the balance (4.1), using a suitable length of filament so that the bottom of the test piece is about 25 mm above the straddle (4.2). The filament shall be made from a material which is insoluble in water and which does not absorb a significant amount of water. It shall either be counterbalanced or be weighed and, if weighed, its mass shall be deducted from subsequent weighings of the test piece (see note 1).

Weigh the test piece to the nearest milligram in air. Repeat the weighing with the test piece (and sinker, if required, see note 2) immersed in freshly boiled and cooled distilled water at a standard temperature ( $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ) contained in the beaker (4.3), placed on the straddle. Remove air bubbles adhering to the test piece (see note 4) and determine the mass to the nearest milligram, watching the pointer for a few

seconds to make sure that it does not drift gradually as a result of convection currents.

### NOTES

1 Where the filament used has a mass less than 0,010 g, such as is the case with thin nylon filament, the correction to account for its mass is not necessary to ensure the stated accuracy of the final result. However, when the test piece is smaller than the one specified (e.g. when the density of small O-rings is to be measured), this can lead to inaccuracies and the mass of the filament needs to be taken into account in the final calculation. If a means of suspension other than a filament is used, the volume and mass of the suspension must be taken into account in making the final calculation.

2 When this procedure is used for rubber having a density less than  $1\text{ Mg/m}^3$ , a sinker is necessary; a further weighing of the sinker alone in water is required. Alternatively, a liquid of different density to water may be used in place of the water, in which case the formulae given in 10.1 are modified by the multiplication of the expression by the density of the liquid expressed in megagrams per cubic metre.

3 The main sources of error are

- air bubbles adhering to the surfaces of the test piece during weighings in water;
- surface tension effects on the filament;
- convection currents in the water in which the test piece is suspended, to minimize which the temperature of the water and of the air in the balance case should be the same.

4 In order to minimize the adherence of air bubbles to the test piece, it is permissible either to add a trace (say 1 part in 10 000) of surface active material such as a detergent to the distilled water or to dip the test piece momentarily into a suitable liquid, such as methyl alcohol or industrial methylated spirits, miscible with water and having a negligible swelling or leaching action on rubber. If the latter method is adopted, precautions should be taken to minimize the carry-over of alcohol.

### 9.3 Method B

Weigh the clean, dry density bottle and stopper (4.4) before and after the insertion of the test piece (clause 5) cut into suitable pieces. The exact size and shape of the pieces will depend on the thickness of the original test piece. They should be such that no two dimensions are greater than 4 mm and the third not greater than 6 mm. Within these limitations the pieces should be as large as possible. All cut edges shall be smooth. Fill the bottle, containing the rubber, completely with freshly boiled and cooled distilled water at a standard temperature ( $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  or  $27\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ). Remove air bubbles adhering to the rubber or to the walls of the bottle (see note 4 above).

Insert the stopper, taking care that there is no air in the bottle or the capillary. Dry the outside of the bottle carefully. Weigh the bottle and contents. Empty the bottle completely and refill with freshly boiled and cooled distilled water. After removing the air bubbles, inserting the stopper and drying, weigh the bottle and water.

All the above weighings shall be made to the nearest milligram.

**NOTE** — The main source of error is air bubbles inside the bottle. It may be necessary to heat the bottle and contents to approximately  $50\text{ }^{\circ}\text{C}$  to dislodge bubbles, but in this case the bottle and contents must be cooled before weighing. Alternatively, the bottle may be placed in a vacuum desiccator and the vacuum applied and released several times until no more air is extracted.

## 10 Expression of results

### 10.1 Method A

The density  $\rho$ , expressed in megagrams per cubic metre, is given by the formula

$$\frac{m_1}{m_1 - m_2}$$

where

$m_1$  is the net mass of the rubber;

$m_2$  is the mass of the rubber less the mass of an equal volume of water, determined by weighing in water, both at the standard temperature.

This method is accurate to the nearest unit in the second place of decimals.

The density of water at standard laboratory temperature may be taken as 1,00 Mg/m<sup>3</sup>.

#### NOTES

1 When a sinker has been used, the calculation must be modified as follows :

$$\rho = \frac{m_1}{m_1 + m_2 - m_3}$$

where

$m_1$  is the net mass of the rubber;

$m_2$  is the mass of the sinker less the mass of an equal volume of water, determined by weighing in water;

$m_3$  is the mass of the sinker and rubber less the mass of a volume of water equal to their combined volumes, determined by weighing in water.

2 For precise work, a factor to take account of the density of water at the test temperature should be used.

### 10.2 Method B

The density  $\rho$ , expressed in megagrams per cubic metre, is given by the formula

$$\frac{m_2 - m_1}{m_4 - m_3 + m_2 - m_1}$$

where

$m_1$  is the mass of the density bottle;

$m_2$  is the mass of the density bottle plus test piece;

$m_3$  is the mass of the density bottle plus test piece plus water;

$m_4$  is the mass of the density bottle filled with water.

NOTE — For precise work, a factor to take account of the density of water at the test temperature should be used.

## 11 Test report

The test report shall include the following particulars :

- a) a reference to this International Standard;
- b) the mean density;
- c) the temperature of test;
- d) the method used (method A or method B);
- e) any deviations from the procedure specified in this International Standard.



## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS.

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc: No. PCD 13 (1986).

### Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

## BUREAU OF INDIAN STANDARDS

### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002  
Telephones: 2323 0131, 2323 3375, 2323 9402

Telegrams: Manaksanstha  
(Common to all offices)

### Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg  
NEW DELHI 110002

Telephone

{ 2323 7617  
2323 3841

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Kankurgachi  
KOLKATA 700054

{ 2337 8499, 2337 8561  
2337 8626, 2337 9120

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 3843  
60 9285

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

{ 2254 1216, 2254 1442  
2254 2519, 2254 2315

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)  
MUMBAI 400093

{ 2832 9295, 2832 7858  
2832 7891, 2832 7892

Branches : AHMEDABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD.  
GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR.  
NALAGARH. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM. VISAKHAPATNAM.