

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 15524 (2004): Automotive vehicles - Retreading of tyres by the pre-cured process [TED 7: Automotive Tyres, Tubes and Rims]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



भारतीय मानक

स्वचल मोटर वाहन — पूर्व-उपचारित प्रक्रिया द्वारा
टायरों की रिट्रेडिंग — विशिष्टि

Indian Standard

**AUTOMOTIVE VEHICLES — RETREADING OF
TYRES BY THE PRE-CURED PROCESS —
SPECIFICATION**

ICS 83.160.10

© BIS 2004

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

FOREWORD

This Indian Standard was adopted by the Bureau of Indian Standards, after the draft finalized by the Automotive Tyres, Tubes and Rims Sectional Committee had been approved by the Transport Engineering Division Council.

In this standard SI units have been used, the unit of force in Newton (N), of tyre load in kilogram (kg) and of pressure in pascal (Pa). Their relationships are given below for information:

1 kgf	= 9.806 65 N (exactly)
	= 9.81 N (approximately)
	= 10 N (within 2 percent error)
1 kPa	= 0.01 kgf/cm ² (within 2 percent error)
1 kgf/cm ²	= 98.066 kPa.

NOTE — Values of kPa rounded to the nearest practical unit.

The composition of the Committee responsible for formulation of this standard is given in Annex B.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

AUTOMOTIVE VEHICLES — RETREADING OF TYRES BY THE PRE-CURED PROCESS — SPECIFICATION

1 SCOPE

This standard covers the retreading of tyres, by the pre-cured tread process, for passenger cars, light-trucks, trucks and buses, lays down requirements for the casings, the methods of retreading, and the equipment to be used, as well as for the finished product.

2 REFERENCES

The following standards contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below:

<i>IS No.</i>	<i>Title</i>
3400	Methods of test for vulcanized rubber.
(Part 1) : 1987	Tensile stress strain properties (<i>second revision</i>)
(Part 2) : 1995	Hardness (<i>second revision</i>)
(Part 4) : 1987	Accelerated ageing (<i>second revision</i>)
(Part 9) : 1987	Density (<i>second revision</i>)
(Part 17) : 1974	Tear strength — Angular test piece
(Part 22) : 1984	Chemical analysis
4910 (Part 2) : 1989	Tyre yarns, cords and tyre cord warpsheets made from man-made fibres—Method of test: Part 2 Liner density (<i>first revision</i>)
13531 : 1992	Automotive tyres — Tread rubber — Mould cure retreading

3 DEFINITIONS

3.1 For the purpose of this standard the definitions given in IS 13531 shall apply, in addition to the following:

3.1.1 *Buzz-Out*

The buffed area resulting from rasping (buzzing-out) of a spot injury during its preparation for repair.

3.1.2 *Pre-cured Tread Process*

A method of retreading tyres in which a vulcanized rubber tread is bonded to the buffed casing by means of a layer of unvulcanized rubber bonding material that is subsequently vulcanized by the application of heat and pressure.

4 REQUIREMENTS

4.1 Material

Tread rubber and other material used in the retreading of tyres by the pre-cured tread process shall comply with the requirements given in Annex A.

NOTE — As material supplied by different manufacturers are not necessarily interchangeable, the advice of the suppliers of the materials concerned must be sought before materials are interchanged.

4.2 Casings

Casings taken up for retreading shall be classified in accordance with IS 13531.

4.3 Freedom from Defects

When examined in accordance with **8.1**, each casing accepted for retreading shall comply with the following requirements:

- a) Outer surface shall be free from signs of aging, side-wall cracking (other than superficial weather-checking), damage caused by chemicals, oil water, or heat and looseness of the breaker edge.
- b) Inner surface shall be free from damage cords, loose cords and other evidence of under-inflation or run-flat.
- c) Steel bead wires shall show no sign of damage, break, or undue distortion and shall not be exposed.
- d) Casing shall be dry, and shall be free from any sign of inherent carcass defects and permanent irregular deformation.
- e) Tread shall be free from separation that cannot be removed by buffing.

- f) Number and extent of permissible (determined in accordance with defects shall not exceed a combination of the appropriate maximum given in IS 13531).

The through cut shall not exceed the following limits:

- | | |
|--|--|
| <ol style="list-style-type: none"> 1) Crown area 2) Shoulder / side wall | The number of through cuts shall not exceed 3 patches and shall not overlap. |
|--|--|

- g) In the case of steel-reinforced casings, the reinforcement shall be free from rust.
 h) Tyres shall not have large through cuts and breaks that are beyond repairs.

5 REQUIREMENTS FOR THE RETREADING PROCESS

5.1 Method of Retreading

Casings shall be retreaded by an approved pre-cured process that is in accordance with the applicable procedures given in 5.5, 5.6 and 5.7.

5.2 Individual Records

The following details of each casing shall be determined and recorded during processing and this record shall accompany the casing throughout the whole retreading process:

- a) Buffed circumference, buffed width, buffed radius;
- b) Rim width when relevant;
- c) Bag or envelope in which vulcanization is to take place when relevant; and
- d) Number of repairs required.

5.3 Repairs

Permissible defects (as in the specification for mould cure tyre retreading) shall be repaired in accordance with the specification for repairs. All buffing dust shall be removed in such a manner as to prevent contamination of the buffed surface. Casings repaired and cured after buffing shall be rebuffed prior to further processing.

5.4 Buffing

5.4.1 Location

The buffing operation shall be carried out in a separate bay or room, that is so constructed and isolated that no buffing dust can spread to other parts of the factory.

5.4.2 Process

5.4.2.1 Buffing shall be carried out by means of a motor-driven buffing machine. The buffed contour shall be that as recommended by the pre-cured tread manufacturer and shall be achieved by means of a template, or adjustable radius settings. The buffed area

on a casing shall be limited to that area which is to be covered by the pre-cured tread and shoulders shall be of equal circumference. As far as possible shoulders shall not be trimmed to match the pre-cured tread and shall be restricted to the extent recommended by the tyre manufacturer. In any case, excessive trimming results in the exposure of any carcass plies or breaker plies is not permissible. The buff width shall not be wider than the width of pre-cured tread used by 5 mm.

5.4.2.2 The buffed surface shall be uniform, free from particles of loose rubber, foreign objects, moisture furrows, channels and loose plies or breakers and from burn or scroch marks caused during buffing and shall have a smooth finish. The recommended buffed texture is RMA-3.

5.4.2.3 A casing with a shoulder design that incorporating deep scallops shall be so prepared as to provide a firm foundation and support for the pre-cured tread. The alternative and preferred method should be to use a tread design that matches the original design.

5.4.3 Inspection

After buffing, each casing shall be inspected (great care being taken to ensure that the buffed surface does not become contaminated) to ensure compliance with the classification and dimensional requirements and freedom from the following:

- a) Looseness of breaker edge,
- b) Contamination of the buffed surface,
- c) Injuries not detectable or detected before buffing,
- d) Damage or injuries caused by buffing (*see* 5.4.2),
- e) Any other defects (*see* 4.2.1), and
- f) Embedded foreign objects.

Embedded foreign objects shall be removed and all surface cuts and permissible defects shall be buzzed out to firm material before final inspection and authorization of further processing.

5.4.4 Transportation and Storage

Buffed surface shall be protected from contamination, and shall be transported preferably on trolleys avoiding direct contact with the floor and stored in clean areas reserved specifically for such casing. A buffed surface that becomes contaminated shall be re-buffed before further processing of the casing.

5.5 Cementing

5.5.1 Location and Equipment

Cementing shall be carried out in a well-ventilated room or bay, and both the room/bay and the equipment shall be kept clean and free from dust. If the cement is not compatible with cements used in the other

processes, it shall be applied by means of an equipment reserved specifically for the process and after the advise of the suppliers of material.

5.5.2 Application

The cement shall be applied to the buffed surface of a casing as soon as possible after buffing, and in all cases within 12 h of the completion of buffing. A buffed casing left uncemented for more than 12 h shall be re-buffed before further processing so as to remove any oxidation or contamination. In the case of exposed steel cord reinforcement, the steel cord shall be cemented within 15 min of the completion of the reparation of the cord.

5.5.2.1 The cement shall be thoroughly mixed before use, and shall be applied by the method specified by its supplier and so as to ensure uniform coverage over the entire buffed area. If it is to be applied by means of an air-operated spray gun, the air must be completely dry and oil-free. If required the cement may be diluted with SBP spirit or equivalent/solvent. Contaminated petrol shall not be used for diluting. When applied by a brush, a stippling action used and care shall be taken to ensure that the brush does not come into contact with unbuffed surface of the casing or any other contaminated surface.

5.5.2.2 The cement surface shall be checked to ensure freedom from buffing dust, and then allowed to dry (in clean areas reserved specifically for such casings) for the length of time specified by the supplier of the cement. Weaving should be avoided.

5.5.3 Transportation and Storage

Cemented surfaces shall be protected from contamination, and shall be transported clear of the floor and stored in clean areas reserved specifically for such casings. If a casing with cemented surfaces becomes contaminated, the contamination shall be removed and the surface shall be re-cemented before further processing.

5.6 Building and Trend Application

5.6.1 General

A cemented casing shall be built up within the time limit specified by the supplier of the cement. A cemented casing that is not built up with this period, shall be re-cemented before further processing. The cemented surface shall not be handled during the building and tread application. All processing shall be carried out in a clean area reserved specifically for these purposes.

5.6.2 Filling

All buzz-outs shall be filled with a suitable rubber material so stitched as to prevent the entrapment of air,

and the material then trimmed flush and level with the contour of the buffed surface. When necessary, deep scallops in a shoulder shall be built up (with suitable material) as to provide a firm base for the pre-cured tread, and then so stitched as to prevent the entrapment of air.

5.6.3 Bonding Material

The bonding material shall be compatible with the tread rubber used, have a width not less than that of the tread rubber and shall be in sheet form, completely protected by a suitable backing film.

5.6.4 Tread Rubber

The tread rubber (*see* 4.1) shall be in the form of a pre-cured strip, of the appropriate dimensions specified in, and having the appropriate tread design (*see* 6.3) moulded in the surface of the pre-cured tread (or when relevant, of the attached bonding strip) to be bonded to the prepared casing. It shall be clean and shall be treated as specified by its manufacturer.

5.6.5 Application

When bonding material of the type given in 5.6.3 is used, one of the following procedures shall be used to secure it to pre-cured tread rubber and the casing.

- a) Tread rubber shall be laid, tread down, on a clean table, any protective film removed and cement applied to the whole area of the cleaned upper surface. If a brush is used to apply the cement, the brush shall be cleaned. The cement shall be allowed to dry for the period specified by its manufacturer. If the tread belts are supplied with the cement already applied, then the tack of the surface shall be checked as per the specification of the tread manufacturer. In case of insufficient tack, a fresh cement recommended by the manufacturer shall be applied evenly to the whole area of the tread rubber. The cemented tread shall be allowed to dry thoroughly. In case more than one piece of tread rubber has to be applied to the tyre, then all ends shall be cut square and buffed cleaned. However, there shall be no more than 2 pieces with the shorter piece being at least 300 mm in length. The bonding material shall be applied directly to the casing without removing the protective film. No more than one layer of bonding material shall be applied to the casing and the over lap at the joint shall not be more than 5 mm. The bonding material alongwith the protective film shall be stitched on a mechanical builder with low pressure (about 1.4 kg/cm² or 20 psi) as given in 5.6.6.

- b) Bonding material and precured tread rubber shall be measured and using a tool that provides clean cuts, cut to the required length on a clean table reserved specifically for the purpose. The tread rubber shall consist of not more than two pieces. The length of the shorter piece being at least tread rubber shall be laid, tread down, on the clean table and any protective film removed, and cement applied to the whole area of the cleaned upper surface. If a brush is used to apply the cement, the brush shall be clean. The cement shall be allowed to dry for the period specified by its manufacturer.

The exposed surface of the bonding material shall be so fitted as to cover the whole of the cement treated surface of the pre-cured tread and the two components stitched together (avoiding the entrapment of air) with the use of a set of clean rollers and care being taken to avoid contamination. Excess bonding material shall be trimmed off. Protective films shall not be removed until absolutely necessary and no clean surface shall be allowed to become contaminated in any way.

The new rubber shall be so applied as to ensure an even tension around the entire circumference of the tyre. After its application, enough pressure shall be applied to the surface of the pre-cured tread rubber (commencing at the centre) to cause adhesion of the bonding gum to the cemented surface, but not sufficient to cause the new rubber to crawl or to bunch up ahead of the stitching roller. Joints (splices) shall be lined up and secured. Care shall be taken to avoid displacement. The bonding material shall stretch on the mechanical builder with sufficient pressure.

5.6.6 The application of the tread rubber treated as per 5.6.5 shall be carried out by means of a motor driven air inflated machine. Stitching of the bonding material and the tread rubber to the casing shall be done by positive methods like mechanical, pneumatic or hydraulic actuators.

In the case of application as given in 5.6.5 (a), the excess tread rubber shall be cut square and buffed clean. The tread shall not be cut too short or too long but cut in such a manner that there is no residual stress at the splice.

5.6.7 Transportation and Storage

Built up casings shall not be exposed to elevated temperature and care shall be taken to prevent contamination of the tread areas and to prevent distortion or displacement (or both) of the new rubber during storage and transportation.

5.7 Vulcanization

5.7.1 The vulcanization of the built up casing shall be done only with the use of flexible rubber envelopes. The envelopes shall be either of the type which is sealed with a tyre at the shoulder (half skirt) or at the bead (full skirt). The tyres shall be wicked to remove any trapped air between the casings and the envelope by a method recommended by the manufacturer. The casing shall be vulcanized either inflated or uninflated but in any case, in a relaxed and undistorted condition.

5.7.2 Vulcanization Conditions

The conditions of time, temperature and pressure shall be controlled, and shall be followed as recommended by the bonding material manufacturer. These conditions shall be such as to ensure complete vulcanization of the bonding material and complete bonding to each other of the pre-cured tread rubber, bonding material and buffed casing. The temperature shall be uniform throughout the autoclave and pressure shall be so distributed over the tread as to ensure that the bonding material is under uniform pressure.

6 REQUIREMENT FOR RETREADED TYRES

6.1 Freedom from Defects

When examined in accordance with 8.1 each retreaded tyre shall be free from the following:

- a) Unrepaired injuries;
- b) Repairs to injuries other than permitted in terms of 4.2;
- c) Repairs not carried out in accordance with the specification for tyre repairs;
- d) Creasing, buckling and stretching of the carcass or bead;
- e) Uneven flow of bonding material;
- f) Open splices; and
- g) Signs of ply, casing, or tread separation.

6.2 Workmanship

The surface of the tyre shall be clean and free from spew. The outside of the tyre may be treated with a finishing coat.

6.3 Tread

The tyre of tread pattern shall be as specified by the purchaser, shall be suitable for the class of casing (see 4.1), and shall preferably be the same as, or similar to that of the original tread. The centre of the line of the tread shall coincide with the circumferential centre line of the casing and the tee shall show no signs of displacement, or variation in high or shoulder.

6.4 Dimensions

The width of the tread shall be at least 90 percent of that of a new tyre having a similar tread pattern. When measured at the groove nearest to the circumferential centre line of the tyre, the thickness of the undertread and skid depth of the pre-cured treads shall conform to the appropriate values given in Table 1.

Table 1 Dimensions of Tread
(Clause 6.4)

All dimensions in millimetres.

Sl No.	Type of Vehicles	Undertread mm, <i>Min</i>		Skid Depth mm, <i>Min</i>		Traction Highway
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	Passenger car	1	6	7	0	–
ii)	Light commercial vehicle	1	6	8	5	11.0
iii)	Truck and bus tyres:					
a)	less than 900 mm section	2	5	12	0	14.0
b)	Over 900 mm section	2	5	12	5	15.0

6.5 Suitability for Service

6.5.1 When fitted (together with a tube in the case of a non-tubeless tyre) to an appropriate rim and inflated to the recommended pressure, a reconditioned tyre shall recover the correct shape and in the case of a tyre for a passenger car or light commercial vehicle shall

be concentric with the rim and shall be capable of being balanced.

6.6 Adhesion

The adhesion between the buffed surface of the casing, the cushion gum and the pre-cured tread rubber, determined in accordance with 8.2 and shall be at least 14 N/mm of width.

7 MARKING

The retreader's name or source of manufacture or trade name/trade-mark shall appear in legible and durable markings on each retreaded tyre.

8 METHODS OF INSPECTION AND TEST

8.1 Inspection of Original Casings and Retreaded Tyres

Check for compliance with 4.2 and 6.1 by using the relevant method given in IS 13531.

8.2 Adhesion Between Casing and Tread Rubber of Retreaded Tyres

Check for compliance with 4.2 and 6.1 by using the relevant method given in IS 13531.

8.3 Dimensions of Defects and Injuries

Use the relevant method given in IS 13531.

ANNEX A

(Clause 4.1)

RAW MATERIAL REQUIRED FOR PRE-CURED RETREADING PROCESS

A-1 PRE-CURED TREAD RUBBER

A-1.1 Should have a minimum hydro-carbon content of 50 percent to ensure adequate wear performance.

A-1.2 Should have adequate under tread not less than 20 percent of the total tread thickness. The bottom surface of the tread should be well sanded or brushed to RMA-3.

A-1.3 It shall conform to the requirements laid down in Table 2.

A-2 BONDING GUM

A-2.1 Should be made of natural rubber and should have excellent tack. The material shall be protected with proper plastic lining. The cure rate of bonding gum should match the temperature system adopted in the precured bonding chambers.

A-2.2 It shall conform to the requirements laid down in Table 3.

A-3 FILLING MATERIAL

A-3.1 Should have the same characteristics and specifications of the bonding gum material, but in different thickness to suit the filling requirement.

A-3.2 It shall conform to the requirements laid down in Table 3.

A-4 CEMENT

A-4.1 The cure rate of cement should match the temperature system adopted. The cement should have excellent tack. Solution used must enable the cement to dry up within a reasonable time period as specified by the user.

A-4.2 It shall conform to the requirements laid down in Table 4.

A-5 ENVELOPE

Should be made of butyl compounds or any other superior material as agreed between manufacturers and users to resist temperature and frequency of use. It shall be elastic enough for easy application on the tyre.

Table 2 Physical Properties for Pre-cured Tread Rubber
(Clause 4.1)

Sl No. (1)	Test Parameter (2)	Requirements (3)	Method of Test, Ref to Part of IS 3400 (4)
i)	Visual examination:		
a)	Appearance	The material shall have smooth finish without any blemishes like starvation dirty moulding blisters, free from foreign material, porosity. Bottom surface shall be buffed to RMA-3 Standard.	
b)	Trade-mark	Marking on top the tread shall include name of manufacturer/trade-mark and size.	
c)	Tread wear indicators	Each tread shall have tread wear indicators at least 6 Nos. spaced equally around the circumference as per IS 10914.	
d)	Width, thickness and tread base	As agreed to between the manufacturer and the purchaser.	
ii)	Specific gravity, <i>Max</i>	1.14	Part 9
iii)	Hardness IRHD/durometer, shore A	60 – 70	Part 2
iv)	Stress-strain properties:		
a)	300 percent modulus (kg/cm^2), <i>Min</i>	100	Part 1
b)	Tensile strength (kg/cm^2), <i>Min</i>	200	
c)	Elongation at break, percent, <i>Min</i>	400	
v)	Air ageing		Part 4
	Change in physical properties after 120 ± 2 h at $70 \pm 2^\circ\text{C}$		
a)	Hardness IRHD/shore A	± 5 Unit	Part 2
b)	Tensile strength, percent, <i>Max</i>	- 10	Part 1
c)	Elongation at break, percent, <i>Max</i>	- 15	
vi)	Abrasion resistance index, <i>Min</i>	160	Part 3
vii)	Ash content, percent, <i>Max</i>	4	Part 22
viii)	Total rubber hydro-carbon content percent, by mass, <i>Min</i>	50	Part 22
ix)	Angle tear, kgf/mm , <i>Min</i>	7	Part 17

Table 3 Physical Properties for Bonding/Cushion Gum (Independently Curable)
(Clause A-3.2)

SI No.	Properties	Requirements	Method of Test Ref to Part of IS 3400
(1)	(2)	(3)	(4)
i)	Visual examination		
	a) Appearance	The material shall have smooth finish and free from foreign material, cure bits, lumps and blisters, wrinkles and kinks	
	b) Dimensions	Thickness 1.2 mm or as detailed earlier or as agreed upon	
ii)	Specific gravity, <i>Max</i>	1.13	Part 9
iii)	Scorch time, <i>Min</i> (t_5 at $138 \pm 1^\circ\text{C}$) <i>Min</i> t_5 (Time for 5 units rise from minimum viscosity)	3	
iv)	Optimum cure time (t_{90} at $138 \pm 1^\circ\text{C}$), <i>Min</i>	6 to 15 (NOTE — Time must be related with O.C.T. of black vulcanizing cement and as per the system of curing suggested by the manufacturer)	
v)	Hardness IRHD/durometer, shore A	45 to 60	Part 2
vi)	Stress-strain properties		
	a) 300 percent modulus (kg/cm^2), <i>Min</i>	70	Part 1
	b) Tensile strength (kg/cm^2), <i>Min</i>	190	Part 1
	c) Elongation at break percent, <i>Min</i>	500	Part 1
vii)	Angle tear, kgf/mm , <i>Min</i>	5.0	Part 17

Table 4 Physical Properties for Vulcanizing Cement/Solution
(Clause A-4.2)

SI No.	Properties	Requirements	Method of Test, Ref to	
			Part of IS 3400 (4)	Annex (5)
(1)	(2)	(3)		
i)	Visual examination	The cement shall have uniform consistency and no sedimentation.		
ii)	Specific gravity, <i>Max</i>	1.13	Part 9	
iii)	Scorch time, <i>Min</i> (t_5 at $138 \pm 1^\circ\text{C}$) <i>Min</i> t_5 (Time for 5 units rise from minimum viscosity)	3		
iv)	Optimum cure time (t_{90} at $138 \pm 1^\circ\text{C}$) <i>Min</i>	5 to 25		
v)	Hardness IRHD/durometer, shore A	40 to 50	Part 2	
vi)	Stress-strain properties			
	a) 300 percent modulus (kg/cm^2), <i>Min</i>	45	Part 1	
	b) Tensile strength (kg/cm^2), <i>Min</i>	175	Part 1	
	c) Elongation at break percent, <i>Min</i>	500	Part 1	
vii)	Angle tear, kgf/mm , <i>Min</i>	4.0	Part 17	
viii)	Drying : Touch dry time minimum, at 25°C to 40°C and 70 RH, <i>Max</i>			
	a) Spray application	10 to 20 min		
	b) Brush application	30 to 40 min		
ix)	Total solid content, percent by mass <i>Min</i>			
	a) Spray application	8		Annex A
	b) Brush application	10		

NOTE — Test at SI No. 2 to 7 shall be carried out on the test specimen prepared after vulcanization of the base stock after making it free from the solvent.

ANNEX B
(Foreword)
COMMITTEE COMPOSITION

Automotive Tyres, Tubes and Rims Sectional Committee, TED 7

<i>Organization</i>	<i>Representative(s)</i>
Central Institute of Road Transport, Pune	SHRI A. S. LAKRA (<i>Chairman</i>) SHRI B. K. CHAPRA (<i>Alternate</i>)
All India Motor Transport Congress, New Delhi	SHRI CHITTARANJAN DAS
Apollo Tyre Ltd (Representing ATMA), New Delhi	SHRI VIJAY SETHI SHRI RAJIV BUDHIRAJA (<i>Alternate</i>)
Ashok Leyland Ltd, Chennai	SHRI R. C. BALAKRISHNAN SHRI C. SUNDARSANAN (<i>Alternate</i>)
Association of State Road Transport Undertaking, New Delh	DIRECTOR
Automotive Research Association of India, Pune	SHRI P. R. SAJANPAWAR SHRI N. V. KARANATH (<i>Alternate</i>)
Bajaj Auto Ltd, Pune	SHRI C. Y. DESHPANDE SHRI T. M. BALARAMAN (<i>Alternate</i>)
Bajaj Tempo Ltd, Pune	SHRI V. V. DESHPANDE SHRI S. M. PARANJPE (<i>Alternate</i>)
Indian Tyre Technical Advisory Committee, New Delhi	SHRI TOM K. THOMAS SHRI T. FALCAO (<i>Alternate</i>)
Controllerate of Quality Assurance (Vehicles), Ahmednagar	SHRI A. R. KULKARNI MAJOR DEEPAK SHARMA (<i>Alternate</i>)
Defence Research & Development Estt (DRDO), Ahmednagar	SHRI R. C. SETHI SHRI N. KARUPPAIAH (<i>Alternate</i>)
Department of Industry Policy & Promotion, New Delhi	SHRI SUSHIL KUMAR SHRI V. K. JAIN (<i>Alternate</i>)
Directorate General of Supplies & Disposals, New Delhi	SHRI R. C. SHARMA
Escorts Tractors Ltd (Research & Development Centre), Faridabad	SHRI A. V. ALEXANDER SHRI VIVEK GUPTA (<i>Alternate</i>)
Fiat Indian Pvt Ltd, Mumbai	SHRI V. MURUGAN
GKW Ltd, Durgapur	SHRI D. BANDOPADHYAY SHRI B. K. RAY CHAUDHARY (<i>Alternate</i>)
HMT Ltd, Pinjore	SHRI ALOK NIGAM SHRI P. K. AGGARWAL (<i>Alternate</i>)
Hyundai Motor India Ltd, Chennai	SHRI A. P. GANDHI
Maruti Udyog Ltd, Gurgaon	SHRI DEEPAK KUMAR SHRI D. N. DAVE (<i>Alternate</i>)
Mahindra & Mahindra Ltd, Nasik	SHRI KAILASH JAT
Ministry of Defence, Jabalpur	SHRI T. K. BASU SHRI Y. SOMRA (<i>Alternate</i>)
Ministry of Surface Transport (Transport Wing), New Delhi	DIRECTOR TECHNICAL
Ordnance Factory Board, VFJ, Kolkata	SHRI AMIR SINGH SHRI Y. SOMRA (<i>Alternate</i>)
Schrader Duncon Limited, Mumbai	SHRI P. P. PRABHU SHRI P. J. SHETTY (<i>Alternate</i>)
Society of Indian Automobile Manufacturers, New Delhi	SHRI RAJAT NANDI
Tata Engg & Locomotive Co Ltd, Pune	SHRI A. K. MOHABEY SHRI R. M. SRIVASTAVA (<i>Alternate</i>)
Toyata Kirloskar Motor India Ltd, Bangalore	SHRI SACHIO YANAZABI
Tractor Manufacturer's Association, New Delhi	SHRI T. C. GOPALAN SHRI N. L. K. MALHOTRA (<i>Alternate</i>)
Triton Valves Ltd, Mysore	SHRI S. MALLIKAR JUNAIAH SHRI S. RAMESH (<i>Alternate</i>)
Tyre Corporation of India Ltd, Kolkata	SHRI BISWANATH BHATTACHARJEE
Wheels India Ltd, Chennai	SHRI V. CHAKRARAJAN SHRI N. ANBA CHESHIAN (<i>Alternate</i>)
Yamaha Motor India Pvt Ltd, Faridabad	SHRI K. C. JAIN SHRI R. K. GUPTA (<i>Alternate</i>)
BIS Directorate General	SHRI K. K. VASHISTHA, Director and Head (TED) [Representing Director General (<i>Ex-officio</i>)]

Member Secretary
SHRI V. ARUMUGAM
Joint Director (TED), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc: No. **TED 7 (007)**.

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

website : www.bis.org.in

Regional Offices:

	Telephones
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 2323 7617 2323 3841
Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Kankurgachi KOLKATA 700054	{ 2337 8499, 2337 8561 2337 8626, 2337 9120
Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022	{ 260 3843 260 9285
Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113	{ 2254 1216, 2254 1442 2254 2519, 2254 2315
Western : Manakalaya, E9 MIDC, Marol, Andheri (East) MUMBAI 400093	{ 2832 9295, 2832 7858 2832 7891, 2832 7892

Branches : AHMEDABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR. NALAGARH. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM. VISAKHAPATNAM.