

**GUIDELINES
FOR
USE OF SILICA-FUME
IN
RIGID PAVEMENT**



**INDIAN ROADS CONGRESS
2013**

**GUIDELINES
FOR
USE OF SILICA-FUME
IN
RIGID PAVEMENT**

Published by:

INDIAN ROADS CONGRESS

Kama Koti Marg,
Sector-6, R.K. Puram,
New Delhi-110 022

August, 2013

Price : ₹ 200/-
(Plus Packing & Postage)

IRC:114-2013

First Published : August, 2013

(All Rights Reserved. No part of this publication shall be reproduced, translated or transmitted in any form or by any means without the permission of the Indian Roads Congress)

Printed by **India Offset Press, Delhi-110064**

1000 Copies

CONTENTS

	Page No.
Personnel of the Highways Specifications and Standards Committee	i
1. Introduction	1
2. Scope	2
3. Influence of Silica-Fume on the Properties of Fresh Concrete	2
4. Influence of Silica-Fume on the Properties of Hardened Concrete	3
5. Abrasion Resistance of Silica-Fume Concrete	4
6. Stipulation in Indian Standards	5
7. Curing	6
8. Opening to Traffic	6
9. Recommendations for use of Silica-Fume in Rigid Pavement	6
References	7



Digitized by the Internet Archive
in 2014

<https://archive.org/details/govlawiracy2013114>

**PERSONNEL OF THE HIGHWAYS SPECIFICATIONS
AND STANDARDS COMMITTEE**

(As on 19th July, 2013)

1.	Kandasamy, C. (Convenor)	Director General (RD) & Spl. Secy. to Govt. of India, Ministry of Road Transport & Highways Transport Bhavan, New Delhi - 110001.
2.	Patankar, V.L. (Co-Convenor)	Addl. Director General, Ministry of Road Transport & Highways, Transport Bhavan, New Delhi - 110001.
3.	Kumar, Manoj (Member-Secretary)	The Chief Engineer (R) S,R&T, Ministry of Road Transport & Highways, Transport Bhavan, New Delhi
4.	Basu, S.B.	Chief Engineer (Retd.) MoRT&H, New Delhi
5.	Bongirwar, P.L.	Advisor, L & T, Mumbai
6.	Bose, Dr. Sunil	Head FPC Divn. CRRI (Retd.), Faridabad
7.	Duhsaka, Vanlal	Chief Engineer, PWD (Highways), Aizwal (Mizoram)
8.	Gangopadhyay, Dr. S.	Director, Central Road Research Institute, New Delhi
9.	Gupta, D.P.	DG(RD) & AS (Retd.), MoRT&H, New Delhi
10.	Jain, R.K.	Chief Engineer (Retd.) Haryana PWD, Sonipat
11.	Jain, N.S.	Chief Engineer (Retd.), MoRT&H, New Delhi
12.	Jain, S.S.	Professor & Coordinator, Centre of Transportation Engg., IIT Roorke, Roorke
13.	Kadiyali, Dr. L.R.	Chief Executive, L.R. Kadiyali & Associates, New Delhi
14.	Kumar, Ashok	Chief Engineer, (Retd), MoRT&H, New Delhi
15.	Kurian, Jose	Chief Engineer, DTTDC Ltd., New Delhi
16.	Kumar, Mahesh	Engineer-in-Chief, Haryana PWD, Chandigarh
17.	Kumar, Satander	Ex-Scientist, CRRI, New Delhi
18.	Lal, Chaman	Engineer-in-Chief, Haryana State Agriculture, Chandigarh
19.	Manchanda, R.K.	Intercontinental Consultants and Technocrats Pvt. Ltd., New Delhi.
20.	Marwah, S.K.	Addl. Director General, (Retd.), MoRT&H, New Delhi
21.	Pandey, R.K.	Chief Engineer (Planning), MoRT&H, New Delhi
22.	Pateriya, Dr. I.K.	Director (Tech.), National Rural Road Deptt. Agency, (Min. of Rural Deptt.), New Delhi
23.	Pradhan, B.C.	Chief Engineer, National Highways, Bhubaneswar

24. Prasad, D.N. Chief Engineer, (NH), RCD, Patna
25. Rao, P.J. Consulting Engineer, H.No. 399, Sector-19, Faridabad
26. Reddy, K. Siva Engineer-in-Chief (R&B) Admn., Road & Building Deptt. Hyderabad
27. Representative of BRO (Shri B.B. Lal), Dpt. DG, HQ DGBR, New Delhi-110 010
28. Sarkar, Dr. P.K. Professor, Deptt. of Transport Planning, School of Planning & Architecture, New Delhi
29. Sharma, Arun Kumar CEO (Highways), GMR Highways Limited, Bangalore
30. Sharma, M.P. Member (Technical), National Highways Authority of India, New Delhi
31. Sharma, S.C. DG(RD) & AS (Retd.), MoRT&H, New Delhi
32. Sinha, A.V. DG(RD) & SS (Retd.) MoRT&H New Delhi
33. Singh, B.N. Member (Projects), National Highways Authority of India, New Delhi
34. Singh, Nirmal Jit DG (RD) & SS (Retd.), MoRT&H, New Delhi
35. Vasava, S.B. Chief Engineer & Addl. Secretary (Panchayat) Roads & Building Dept., Gandhinagar
36. Yadav, Dr. V.K. Addl. Director General, DGBR, New Delhi

Corresponding Members

1. Bhattacharya, C.C. DG(RD) & AS (Retd.) MoRT&H, New Delhi
2. Das, Dr. Animesh Associate Professor, IIT, Kanpur
3. Justo, Dr. C.E.G. 334, 14th Main, 25th Cross, Banashankari 2nd Stage, Bangalore-560 070.
4. Momin, S.S. (Past President, IRC) 604 A, Israni Tower, Mumbai
5. Pandey, Prof. B.B. Advisor, IIT Kharagpur, Kharagpur

Ex-Officio Members

1. Kandasamy, C. Director General (Road Development) & Special Secretary, MoRT&H and President, IRC, New Delhi
2. Prasad, Vishnu Shankar Secretary General, Indian Roads Congress, New Delhi

1 INTRODUCTION

The silica-fume, a very fine non-crystalline silicon dioxide is a by-product obtained during manufacture of silicon and ferrosilicon alloys from pure quartz and carbon in electric arc furnace. It is also called microsilica or condensed silica-fume. It is a reactive pozzolana. The particles of silica-fume are extremely fine, most of them having diameter in the range of 0.03 and 0.30 micron. The specific surface of such fine particles can not be determined by Blaine's air permeability method. The nitrogen adsorption method (BET method) indicates a specific surface of more than 15 m²/gm. Such a fine material has a very low bulk density of about 200-300 kg/m³. As handling this light powder is difficult, it is densified by condensing with moisture, and then transported. In condensed form, the bulk density of silica-fume is about 500kg/m³. Silica-fume is usually used in concrete in proportion up to 10% by weight of cementitious material in the concrete mix, for development of high strength and abrasion resistance.

Because of high reactivity with calcium hydroxide in concrete, the resulting matrix is very dense and has low permeability. Additional benefits are reduced bleeding and improved cohesion of the concrete mix. Consequently, the porosity of concrete is also reduced.

The Rigid Pavement Committee (H-3) constituted a sub-group comprising Dr. S.C. Maiti, Shri Satander Kumar and Shri J. B. Sengupta for formulation of "Guidelines for Use of Silica Fume in Rigid Pavements". The draft guidelines Prepared by the sub-group was discussed by the Committee in series of meetings. The Rigid Pavement Committee (H-3) finalized the draft guidelines on 10th November, 2012 for placing before the HSS Committee. The Highways Specifications and Standards Committee (HSS) in its meeting held on 13th December, 2012. The Executive Committee in its meeting held on 19th December, 2012 approved this document. Finally, the Council approved this document in their meeting held on 8th January, 2013 at Coimbatore and authorized the Convenor, Rigid Pavement Committee (H-3) to incorporate the comments of Council members and place the same before the HSS Committee before publishing. Accordingly, H-3 Committee modified the draft which was approved by the HSS Committee in its meeting held on 19 July, 2013.

The composition of the Rigid Pavement Committee is given below:

R.K. Jain	-----	Convenor
Satander Kumar	-----	Co-Convenor
Raman Kumar	-----	Member-Secretary

Members

A.K. Jain	Dr. S.S. Seehra
Akhil Kumar Gupta	Isaac V. Joseph
Ashok Kumar	J.B. Sengupta
Ashutosh Gautam	Jose Kurian
B.S. Singla	K. Sitaramanjaneyulu

Bageshwar Prasad	K.K. Gupta
L.K. Jain	Col. V.K. Ganju
M.C. Venkatesh	Dr. B.B. Pandey
P.L. Bongirwar	Dr. L.R. Kadiyali
Prabhat Krishna	Dr. S.C. Maiti
R.N. Sharma	Dr. S.N. Sachdeva
	Rep. of CMA E-in-C Branch

Corresponding Members

Vishal Thombre	D.C. De
Rajesh Madan	S.A. Reddi
Brig. Vinod Nakra	Dr. C.E.G. Justo

Ex-Officio Members

C. Kandasamy	-----	Director General (Rural Development) & Special Secretary, MoRTH & President, IRC
Vishnu Shankar Prasad	-----	Secretary General, IRC

2 SCOPE

Silica fume up to 10 as part replacement (by weight of cementitious materials) is suggested to be used in concrete as per IRC:15 for rigid pavement. Pavement Quality Concrete (PQC) with the use of silica fume shall have minimum flexural strength of 4.5 MPa and the corresponding compressive strength of 40 MPa. Such concrete is very cohesive, has low permeability, is highly abrasion resistant, and has longer service life. This concrete may be used in special cases in State and National Highways especially in coastal regions and where high abrasion resistance is required.

3 INFLUENCE OF SILICA-FUME ON THE PROPERTIES OF FRESH CONCRETE

The very large surface area of the particles of silica fume increases the water demand in concrete mixes. Therefore, it is necessary to use a superplasticizer in the mix. This would make it possible to use low water- cement ratio in concrete, for a given workability. The low water- cement ratio results in increased strength of concrete and reduced permeability.

Concrete mixes with a high content of cementitious materials tend to be sticky and to avoid 'sticky' mix, the water content of concrete mix should not be less than 150 kg/m³ of concrete.

Generally, silica fume is compatible with all superplasticizers. The mixing of such fine powder in concrete should preferably be carried out in an efficient pan or paddle mixer or in a batching and mixing plant as per IS: 4925 and IS: 4926.

4 INFLUENCE OF SILICA-FUME ON PROPERTIES OF HARDENED CONCRETE

Concrete containing silica fume develops early as well as later compressive and flexural strengths of concrete. Typical relationship between water-cementitious materials ratio and 28-day compressive strength of concrete is shown in **Fig. 1**.




Fig. 1: Typical Results for Strength Improvement

The presence of silica-fume in concrete has a beneficial effect upon resistance to abrasion because, in the absence of bleeding, no weak top layer is formed, and also because of a better bond between the hydrated cement paste and the coarse aggregate, differential wear and loosening of particles do not occur.

5 ABRASION RESISTANCE OF SILICA-FUME CONCRETE

Low water-cement ratio high-strength silica-fume concrete shows greatly improved resistance to abrasion with low permeability. Abrasion resistance is an important area of application for silica-fume concrete such as at Toll Plaza and curves and where there is frequent change of grade (hill road). When the road is to be used by steel tyred or tracked vehicle, such as iron-tyred bullock carts, military tanks etc. as per IRC:15, use of silica-fume concrete for abrasion resistance has been recommended. This helps in reducing Foreign Object Damage (FOD) problem in airfield pavement also. The Norwegian practice of using studded tyres on cars during winter causes extreme wear of the road surface. Thus, in recent years, high-strength abrasion -resistant silica-fume concrete has become the paving material of choice, for high wear resistance. The Southern Illinois University test results indicate more than 100% improvement in abrasion resistance (abrasion index) with 10% silica-fume in concrete (**Fig. 2**) using ASTM C779 abrasion resistance test for horizontal surfaces (Ball revolution test method).

The abrasion index, as defined by the Australian Paving Association, given below may be adopted for determining the abrasion index:

$$IA = \frac{R^{1/2}}{P}$$

Where,

- IA = Abrasion Index
- R = Ball race revolution, in thousands,
- P = Depth of wear, in mm.




Fig. 2: Abrasion Index of Silica Fume Concrete (5 minutes testing period)

Their recommendation based on 5000 ball revolution for different traffic conditions are as follows:-

	Traffic condition		Abrasion Index
i)	For busy footpaths and malls with heavy pedestrian traffic	-	51
ii)	Public roadways	-	38
iii)	Car parking & vehicular traffic	-	31

These Guidelines recommend an abrasion index of 50 for rigid pavements.

6 STIPULATIONS IN INDIAN STANDARDS

IRC:15 stipulates use of silica-fume (as per IS: 15388, IS: 456 and IRC:SP:70 in concrete up to 10 percent by weight of cementitious materials. IRC:SP:70-2005 stipulate use of silica-fume in concrete to develop High Performance Concrete in bridges. The Indian Standard specification for silica-fume IS: 15388 covers the chemical and physical requirements of silica-fume for use in concrete.

The chemical and physical properties shall be as per **Table 1** and **Table 2** respectively.

Table 1 : Chemical Requirements of Silica-Fume

(As per IS: 15388)

SI. No.	Characteristics	Requirement	Test Method
1)	SiO ₂ percent by mass, min	85.0	IS: 1727
2)	Moisture Content, percent by mass, Max.	3.0	-
3)	Loss on ignition, percent by mass Max.	4.0	IS: 1727
4)	Alkalies as Na ₂ O, percent, max.	1.5	-

Table 2: Physical Requirements of Silica-Fume

(As per IS: 15388)

SI.No.	Characteristics	Requirement	Test Method
i)	Specific surface, m ² /gm, Min.	15	BET Method, IS: 15388
ii)	Oversize, percent retained on 45 micron IS sieve, Max.	10	IS: 1727
iii)	Oversize, percent retained on 45 micron IS sieve, variation from average percent, Max.	5	IS: 1727
iv)	Compressive strength at 7 days as percent of control sample, Min.	85	IS: 1727

Notes:

- 1) Any one of the tests specified in (i) or (ii) and (iii) may be adopted.
- 2) For (iii), the average of 10 preceding tests or all of the preceding tests, if the number is less than 10.
- 3) For (iv), in accordance with the test method of IS: 1727, the value of factor N may be taken as 1, where
$$N = \frac{\text{specific gravity of silica-fume}}{\text{specific gravity of cement}}$$

7 CURING

Immediately after the finishing operations have been completed, the entire surface of the newly laid concrete shall be covered against rapid drying, and cured as per IRC:15.

Curing shall be done by one of the following two methods:

- i) By application of curing compound is followed by spreading of wet hessian cloth and moistening it regularly. In case of arid areas where water is extremely scarce, two applications of curing compound with moist curing by wet hessian cloth may be allowed at the discretion of the Engineer-in-Charge. Curing compound shall be resin based aluminized reflective type.
- ii) For small works, curing can be done by manual methods using wet hessian cloth which is kept moist during curing period.
- iii) Curing shall be done for a minimum period of 16 days.
- iv) The water used for curing shall also be free from all injurious chemicals, like, chlorides and sulphates and shall meet the requirements of IS:456.

8 OPENING TO TRAFFIC

In general, traffic shall not use newly constructed pavement for a minimum period of 28 days as per IRC:15.

9 RECOMMENDATIONS FOR USE OF SILICA-FUME IN RIGID PAVEMENT

Because of good abrasion-resistant properties of silica-fume concrete, its use in rigid pavement is recommended. The concrete having 40 or 45 MPa compressive strength (4.5 or 5 MPa flexural strength), although has good resistance to abrasion, it is suggested that such concrete should include silica-fume upto 10 as part replacement of cementitious material, so that with better strength and abrasion-resistance characteristics of silica-fume concrete, the service life of the rigid pavements can be enhanced.

Because of part replacement of cement, and because of additional strength characteristics, the silica-fume concrete will not be very costly, as the reduction of cement will be higher than the percentage of silica-fume used, for the required flexural strength of concrete. The silica-fume concrete, however, will need more curing, than that required for normal concrete pavement, as is the case for concrete with all pozzolanic materials. In order to obtain improved abrasion resistance of concrete pavement with silica-fume, it is suggested to adopt a longer curing period.

The requirement of construction methodology, quality control, mix design and other requirement not covered above shall be followed as per IRC:15 and IRC:44.

REFERENCES

- 1) IRC:15:2011 Standard Specifications and Code of Practice for Construction of Concrete Roads. Indian Roads Congress, New Delhi.
- 2) IS: 4925-1968 Indian Standard Specification for Concrete Batching and Mixing Plant, Bureau of Indian Standards, New Delhi.
- 3) IS: 4926-2003 Indian Standard Code of Practice for Ready-Mixed Concrete. Bureau of Indian Standards, New Delhi.
- 4) FIDJESTOL, P. and LEWIS, ROBERT, Microsilica as an addition, in Lea's Chemistry of Cement and Concrete, 4th Edition, Elsevier Limited, 1998, pp.679-712.
- 5) GHAFOORI, N. and DIAWARA, H. Abrasion Resistance of Fine Aggregate Replaced Silica-Fume Concrete. ACI Materials Journal, September-October 1999, pp 559-567.
- 6) ASTM C 779 Abrasion Resistance for Horizontal Concrete Surface. American Society for Testing and Materials, Philadelphia.
- 7) IS:15388-2003 Indian Standard Specification for Silica Fume. Bureau of Indian Standards, New Delhi.
- 8) IS:456-2000 Code of Practice for Plain and Reinforced Concrete. Bureau of Indian Standards, New Delhi.
- 9) IRC:SP:70-2005 Guidelines for the Use of High Performance Concrete in Bridges. Indian Roads Congress, New Delhi.
- 10) IS: 1727-1967 Methods of Test for Pozzolanic Materials (First Revision), Bureau of Indian Standards, New Delhi.
- 11) IRC:44-2008 Guidelines for Cement Concrete Mix Design for Pavements (Second Revision), Indian Roads Congress, New Delhi.

(The Official amendments to this document would be published by the IRC in its periodical, 'Indian Highways' which shall be considered as effective and as part of the code/guidelines/manual, etc. from the date specified therein)